

COPY

FP04-0242-00

DESCRIPTION

REFRIGERATING MACHINE OIL COMPOSITION

Technical Field

5 [0001] The present invention relates to a refrigerating machine oil composition for use in compressors of refrigerating/air conditioning devices.

Background Art

10 [0002] With the shift from ozone layer-depleting chlorofluorocarbons toward refrigerant substitutes in accordance with the Montreal Protocol, much research is being carried out on refrigerating machine oils suitable for such refrigerant substitutes. Refrigerating machine oils used for hydrofluorocarbon (HFC) refrigerants, for example, include synthetic oils
15 such as polyol esters and ethers, which are miscible with HFC refrigerants (for example, see Patent Documents 1-3).

[Patent Document 1] Japanese Patent Public Inspection
HEI No. 3-505602

20 [Patent Document 2] Japanese Unexamined Patent Publication HEI No. 3-128992

[Patent Document 3] Japanese Unexamined Patent Publication HEI No. 3-200895

Disclosure of the Invention

25 [0003] When such conventional refrigerating machine oils comprising oxygen-based synthetic oils are used,

BEST AVAILABLE¹ COPY

COPY

however, the lower lubricity of such refrigerating machine oils compared to that of mineral oil-based refrigerating machine oils, combined with the lower lubricity of refrigerant substitutes used with them compared to that of ozone layer-depleting chlorofluorocarbons, tends to contribute to unstable operation of the refrigerating/air conditioning device, and a shorter usable life of the apparatus.

[0004] The present invention has been accomplished in light of the aforementioned problems of the prior art, and its object is to provide a refrigerating machine oil composition which exhibits excellent lubricity for refrigerating/air conditioning devices employing refrigerants such as HFCs, and allows the refrigerating/air conditioning devices to be operated in a stable manner for prolonged periods.

[0005] In order to achieve this object, the invention provides a refrigerating machine oil composition comprising a prescribed base oil, a phosphorus-based extreme pressure agent and an ester-based additive.

[0006] By using a phosphorus-based extreme pressure agent in combination with an oil agent in the refrigerating machine oil composition of the invention, both the abrasion resistance and friction properties of the refrigerating machine oil composition are

adequately enhanced, thereby allowing stable operation of the refrigerating/air conditioning device for prolonged periods even for use in combination with refrigerants such as HFCs.

5 [0007] Since the enhancing effect of the refrigerating machine oil composition of the invention on the abrasion resistance and friction properties also contributes to improved energy efficiency of the refrigerating/air conditioning device, it is also
10 highly advantageous from the standpoint of energy saving and of reducing production costs for the refrigerating/air conditioning device. Specifically, reduction in abrasion and friction due to refrigerating machine oils in conventional refrigerating/air
15 conditioning devices has not been adequately studied, and most attempts to improve abrasion resistance or friction properties have relied on modifying the hard components such as the compressor, since adverse effects by abrasion resistance enhancers or oil agents is a concern. However, the refrigerating machine oil
20 composition of the invention adequately reduces the sliding load in the compressor due to its excellent abrasion resistance and friction properties, and it can therefore improve energy efficiency of
25 refrigerating/air conditioning devices even without modifying hard components such as the compressor or

heat exchanger. In addition, the enhancing effect on abrasion resistance and friction properties according to the invention allows low material grade sliding members, i.e. cheaper sliding members, to be used as the sliding members for the compressor, thereby realizing a cost reduction for the refrigerating/air conditioning device. Furthermore, by combining the refrigerating machine oil composition of the invention with an abrasion resistance-enhanced compressor or the like, it is possible to achieve a drastic improvement in energy efficiency.

[0008] The enhancing effect of the refrigerating machine oil composition of the invention on the abrasion resistance and friction properties is only obtained by using a phosphorus-based extreme pressure agent in combination with an oil agent, and the enhancing effect is remarkable compared to using either a phosphorus-based extreme pressure agent or an oil agent alone. For example, when an oil agent alone among the aforementioned additives is used in a refrigerating machine oil for an HFC-based refrigerant, the enhancing effect on abrasion resistance and friction properties is often inadequate, or in some cases the thermal-oxidative stability or the refrigerant atmosphere/low temperature anti-separation property of the refrigerating machine oil are impaired.

When an extreme pressure agent such as a phosphorus-based compound is used alone, the friction properties are sometimes inferior. The refrigerating machine oil composition of the invention, on the other hand, allows these properties to be maintained at a high level.

[0009] The term "phosphorus-based extreme pressure agent" used according to the invention encompasses phosphorus-based additives such as phosphoric acid esters, acidic phosphoric acid esters, acidic phosphoric acid ester amines, chlorinated phosphoric acid esters and phosphorous acid esters, as well as phosphorothionates (thiophosphoric acid esters).

[0010] The phosphorus-based extreme pressure agent in the refrigerating machine oil composition of the invention preferably contains a phosphorothionate. Combination of a phosphorothionate with an oil agent will allow a satisfactory balance to be achieved with high levels of both abrasion resistance and friction properties of the refrigerating machine oil composition.

[0011] The phosphorus-based extreme pressure agent in the refrigerating machine oil composition of the invention preferably contains both a phosphorothionate and a phosphorus-based extreme pressure agent other than a phosphorothionate. The aforementioned effect of the invention will thereby be exhibited at an even higher level due to the synergistic effect of the

phosphorothionate and the phosphorus-based extreme pressure agent other than the phosphorothionate, as well as the synergistic effect between each of the phosphorus-based extreme pressure agents and the oil agent, thereby providing further enhancement particularly of the friction properties.

[0012] The refrigerating machine oil composition of the invention preferably further contains an epoxy compound. Combination of a phosphorus-based extreme pressure agent, an oil agent and an epoxy compound will allow the aforementioned effect of the invention to be exhibited at an even higher level, and is effective particularly from the standpoint of further enhancing the friction properties.

[0013] The oil agent in the refrigerating machine oil composition of the invention preferably contains an ester oil agent. The aforementioned effect of the invention will thereby be exhibited at an even higher level due to the synergistic effect of the phosphorus-based extreme pressure agent and the ester oil agent.

[0014] The oil agent in the refrigerating machine oil composition of the invention preferably comprises at least one compound selected from among esters of monobasic acids and monohydric alcohols and esters of linear dibasic acids and monohydric alcohols, and more preferably it comprises at least one compound selected

from among $\geq C_{12}$ esters of monobasic acids and monohydric alcohols and esters of linear dibasic acids and monohydric alcohols. Using such an oil agent can further enhance the abrasion resistance and friction properties.

[0015] The oil agent in the refrigerating machine oil composition of the invention includes an ester oil agent, and the content of the ester oil agent is preferably 0.01-10 wt% based on the total weight of the composition. An ester oil agent content within this range will enhance not only the abrasion resistance and friction properties, but also the thermal-oxidative stability.

[0016] Preferably, the base oil in the refrigerating machine oil composition of the invention comprises at least one compound selected from among esters of polyhydric alcohols and monobasic fatty acids and esters of alicyclic dibasic acids and monohydric alcohols, and the oil agent comprises at least one compound selected from among esters of monobasic acids and monohydric alcohols and esters of linear dibasic acids and monohydric alcohols. Such a combination of an ester-based base oil and an ester oil agent can further enhance the abrasion resistance and friction properties, as well as the refrigerant atmosphere/low temperature anti-separation property.

[0017] By using the refrigerating machine oil composition of the invention it is possible to achieve excellent lubricity for refrigerating/air conditioning devices employing refrigerants such as HFCs, thus allowing refrigerating/air conditioning devices to be operated in a stable manner for prolonged periods.

Best Mode for Carrying Out the Invention

[0018] A preferred mode of the invention will now be explained in detail.

10 [0019] (Base oil)

[0020] The base oil used for the invention may be a mineral oil or synthetic oil, or it may be a mixed-base oil comprising a mineral oil and a synthetic oil.

15 [0021] As examples of mineral oils there may be mentioned paraffin-based mineral oils or naphthene-based mineral oils obtained by applying an appropriate combination of one or more purifying means from among solvent deasphalting, solvent extraction, hydrocracking, solvent dewaxing, catalytic dewaxing, hydrorefining, sulfuric acid washing and clay treatment, to lube-oil distillates obtained by atmospheric distillation and vacuum distillation of paraffin base crude oils, intermediate base crude oils or naphthene base crude oils.

25 [0022] Among such mineral oils, it is preferred to use mineral oils which have been highly purified

(hereinafter referred to as "highly purified mineral oils"), from the standpoint achieving superior thermal stability. As specific examples of highly purified mineral oils there may be mentioned purified oils obtained using ordinary methods to purify oil distillates prepared by atmospheric distillation of, or vacuum distillation of the oil residue from atmospheric distillation of, paraffin base crude oils, intermediate base crude oils or naphthene base crude oils; deep dewaxed oils obtained by further deep dewaxing treatment after purification; and hydrogenated oils obtained by hydrogenation treatment.

[0023] There are no particular restrictions on the purification method used for this purification step, and any conventional publicly known method may be employed; as examples, however, there may be mentioned (a) hydrogenation treatment, (b) dewaxing treatment (solvent dewaxing or hydrogenated dewaxing), (c) solvent extraction treatment, (d) alkali washing or sulfuric acid washing treatment and (e) clay treatment, either alone or in combinations of two or more in a suitable order. It is effective to repeatedly carry out a treatment from among treatments (a) to (e) above over multiple stages. More specifically, there may be mentioned (i) a method of hydrogenation treatment of the oil distillate or a method of hydrogenation

treatment followed by alkali washing or sulfuric acid washing; (ii) a method of hydrogenation treatment of the oil distillate followed by dewaxing treatment; (iii) a method of solvent extraction of the oil distillate followed by hydrogenation treatment; (iv) a method of two-stage or three-stage hydrogenation treatment of the oil distillate, optionally followed by alkali washing or sulfuric acid washing treatment; and (v) any of the aforementioned methods (i) to (iv) followed by further dewaxing treatment to obtain a deep dewaxed oil.

[0024] Among highly purified mineral oils obtained by these purification methods, naphthene-based mineral oils and minerals oils obtained by deep dewaxing treatment are preferred from the standpoint of low-temperature flow properties and of preventing wax separation at low temperature. The deep dewaxing treatment will ordinarily be carried out by solvent dewaxing treatment under stringent conditions, or catalytic dewaxing treatment using a zeolite catalyst.

[0025] The non-aromatic unsaturated portion (degree of unsaturation) of the highly purified mineral oil is preferably no greater than 10 wt%, more preferably no greater than 5 wt%, even more preferably no greater than 1 wt% and most preferably no greater than 0.1 wt%. A non-aromatic unsaturated portion of greater than 10

wt% will result in greater sludge production, which will tend to clog the expansion mechanisms such as capillaries of the refrigerant circulation system.

[0026] As synthetic oils to be used for the invention there may be mentioned hydrocarbon-based oils such as olefin polymers, naphthalene compounds and alkylbenzenes, and oxygen-containing synthetic oils such as esters, polyoxyalkylene glycols, polyvinyl ethers, ketones, polyphenyl ethers, silicones, polysiloxanes and perfluoroethers.

[0027] As olefin polymers there may be mentioned those obtained by polymerization of C2-12 olefins, as well as hydrogenated products of the compounds obtained by such polymerization, and preferred for use are polybutene, polyisobutene, C5-12 α -olefin oligomers (poly α -olefins), ethylene-propylene copolymers and hydrogenated products thereof.

[0028] There are no particular restrictions on the method of producing olefin polymers, and any of various publicly known methods may be employed. For example, poly α -olefins are produced by treatment of ethylene-derived α -olefin starting materials by publicly known polymerization methods such as Ziegler catalyst methods, radical polymerization methods, aluminum chloride methods, boron fluoride methods or the like.

[0029] There are no particular restrictions on the

naphthalene compound so long as it includes a naphthalene skeleton, but from the standpoint of excellent miscibility with refrigerants, it is preferably one having one to four C1-10 alkyl groups, with a total of 1-10 carbon atoms of the alkyl groups, and is more preferably one having one to three C1-8 alkyl groups, with a total of 3-8 carbon atoms of the alkyl groups.

[0030] As specific examples of C1-10 alkyl groups for the naphthalene compound there may be mentioned methyl, ethyl, n-propyl, isopropyl, straight-chain or branched butyl, straight-chain or branched pentyl, straight-chain or branched hexyl, straight-chain or branched heptyl, straight-chain or branched octyl, straight-chain or branched nonyl and straight-chain or branched decyl.

[0031] When a naphthalene compound is used, one compound with a specific structure may be used alone, or two or more compounds with different structures may be used in combination.

[0032] There are no particular restrictions on the method of producing the naphthalene compound, and any of various publicly known methods may be employed. As examples there may be mentioned a method wherein a C1-10 hydrocarbon halide, C2-10 olefin or C8-10 styrene is added to naphthalene in the presence of an acidic

catalyst, e.g. a mineral acid such as sulfuric acid, phosphoric acid, tungstosilicic acid or hydrofluoric acid, a solid acidic substance such as acidic white clay or active white clay, or a metal halide Friedel-Crafts catalyst such as aluminum chloride or zinc chloride.

[0033] There are no particular restrictions on an alkylbenzene used for the invention, but from the standpoint of excellent miscibility with refrigerants it is preferably one having one to four C1-40 alkyl groups, with a total of 1-40 carbon atoms of the alkyl groups, and is more preferably one having one to four C1-30 alkyl groups, with a total of 3-30 carbon atoms of the alkyl groups.

[0034] As specific examples of C1-40 alkyl groups for the alkylbenzene compound there may be mentioned methyl, ethyl, n-propyl, isopropyl, straight-chain or branched butyl, straight-chain or branched pentyl, straight-chain or branched hexyl, straight-chain or branched heptyl, straight-chain or branched octyl, straight-chain or branched nonyl, straight-chain or branched decyl, straight-chain or branched undecyl, straight-chain or branched dodecyl, straight-chain or branched tridecyl, straight-chain or branched tetradecyl, straight-chain or branched pentadecyl, straight-chain or branched hexadecyl, straight-chain or

branched heptadecyl, straight-chain or branched
 octadecyl, straight-chain or branched nonadecyl,
 straight-chain or branched eicosyl, straight-chain or
 branched heneicosyl, straight-chain or branched docosyl,
 5 straight-chain or branched tricosyl, straight-chain or
 branched tetracosyl, straight-chain or branched
 pentacosyl, straight-chain or branched hexacosyl,
 straight-chain or branched heptacosyl, straight-chain
 or branched octacosyl, straight-chain or branched
 10 nonacosyl, straight-chain or branched triacontyl,
 straight-chain or branched hentriacontyl, straight-
 chain or branched dotriacontyl, straight-chain or
 branched tritriacontyl, straight-chain or branched
 tetratriacontyl, straight-chain or branched
 15 pentatriacontyl, straight-chain or branched
 hexatriacontyl, straight-chain or branched
 heptatriacontyl, straight-chain or branched
 octatriacontyl, straight-chain or branched
 nonatriacontyl and straight-chain or branched
 20 tetracontyl (including all isomers thereof).

[0035] Although the aforementioned alkyl groups may
 be straight-chain or branched, they are preferably
 straight-chain alkyl groups from the standpoint of
 miscibility with organic materials used in the
 25 refrigerant circulation system. From the standpoint of
 refrigerant miscibility, thermal stability and

lubricity, however, branched alkyl groups are preferred, while from the standpoint of availability, branched alkyl groups derived from oligomers of olefins such as propylene, butene and isobutylene are more preferred.

5 [0036] When an alkylbenzene is used, one compound with a specific structure may be used alone, or two or more compounds with different structures may be used in combination.

10 [0037] Any alkylbenzene production process may be employed with no restrictions whatsoever, and the synthesis method outlined below may be set forth as an example.

15 [0038] As aromatic starting compounds there may be used, specifically, benzene, toluene, xylene, ethylbenzene, methylethylbenzene, diethylbenzene, and mixtures thereof. As alkylating agents there may be used C6-40 straight-chain or branched olefins obtained by polymerization of lower monoolefins such as ethylene, propylene, butene or isobutylene (preferably
20 propylene); C6-40 straight-chain or branched olefins obtained by thermal decomposition of waxes, heavy oils, petroleum fractions, polyethylene, polypropylene and the like; C9-40 straight-chain olefins obtained by separation of n-paraffin from petroleum fractions such
25 as kerosene and light oil, and olefination thereof with a catalyst; as well as mixtures of these.

[0039] The reaction between the aforementioned aromatic compound and alkylating agent may be conducted using a conventional publicly known alkylation catalyst, e.g. a Friedel-Crafts catalyst such as aluminum chloride or zinc chloride, or an acidic catalyst such as sulfuric acid, phosphoric acid, tungstosilicic acid, hydrofluoric acid, or acidic white clay.

[0040] Examples of esters include aromatic esters, dibasic acid esters, polyol esters, complex esters, carbonic acid esters, and mixtures thereof.

[0041] As aromatic esters there may be mentioned esters of monobasic to hexabasic, preferably dibasic to tetrabasic and more preferably monobasic to tribasic aromatic carboxylic acids with C1-18 and preferably C1-12 aliphatic alcohols. As specific monobasic to hexabasic aromatic carboxylic acids there may be mentioned benzoic acid, phthalic acid, isophthalic acid, terephthalic acid, trimellitic acid, pyromellitic acid, and mixtures thereof. The C1-18 aliphatic alcohols may be straight-chain or branched, and specifically there may be mentioned methanol, ethanol, straight-chain or branched propanol, straight-chain or branched butanol, straight-chain or branched pentanol, straight-chain or branched hexanol, straight-chain or branched heptanol, straight-chain or branched octanol, straight-chain or branched nonanol, straight-chain or branched decanol,

straight-chain or branched undecanol, straight-chain or branched dodecanol, straight-chain or branched tridecanol, straight-chain or branched tetradecanol, straight-chain or branched pentadecanol, straight-chain or branched hexadecanol, straight-chain or branched heptadecanol, straight-chain or branched octadecanol, and mixtures thereof.

[0042] As specific aromatic esters obtained using the aforementioned aromatic compounds and aliphatic alcohols there may be mentioned dibutyl phthalate, di(2-ethylhexyl) phthalate, dinonyl phthalate, didodecyl phthalate, ditridecyl phthalate, tributyl trimellitate, tri(2-ethylhexyl) trimellitate, trinonyl trimellitate, tridecyl trimellitate, tridodecyl trimellitate and tritridecyl trimellitate. Needless to mention, when a dibasic or greater aromatic carboxylic acid is used, the ester may be a simple ester comprising one type of aliphatic alcohol, or it may be a complex ester comprising two or more different aliphatic alcohols.

[0043] As dibasic acid esters there are preferably used esters of C5-10 linear or cyclic aliphatic dibasic acids such as glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, 1,2-cyclohexanedicarboxylic acid and 4-cyclohexene-1,2-dicarboxylic acid, with straight-chain or branched C1-

15 monohydric alcohols such as methanol, ethanol,
propanol, butanol, pentanol, hexanol, heptanol, octanol,
nonanol, decanol, undecanol, dodecanol, tridecanol,
tetradecanol and pentadecanol, as well as mixtures
5 thereof, among which there may be mentioned
specifically ditridecyl glutarate, di-2-ethylhexyl
adipate, diisodecyl adipate, ditridecyl adipate, di-2-
ethylhexyl sebacate, diesters of 1,2-
cyclohexanedicarboxylic acid with C4-9 monohydric
10 alcohols, diesters of 4-cyclohexene-1,2-dicarboxylic
acid with C4-9 monohydric alcohols, and mixtures
thereof.

[0044] As polyol esters to be used there are
preferred esters of C6-20 fatty acids with diols or
15 with polyols containing 3-20 hydroxyl groups. As
specific diols there may be mentioned ethylene glycol,
1,3-propanediol, propylene glycol, 1,4-butanediol, 1,2-
butanediol, 2-methyl-1,3-propanediol, 1,5-pentanediol,
neopentyl glycol, 1,6-hexanediol, 2-ethyl-2-methyl-1,3-
20 propanediol, 1,7-heptanediol, 2-methyl-2-propyl-1,3-
propanediol, 2,2-diethyl-1,3-propanediol, 1,8-
octanediol, 1,9-nonanediol, 1,10-decanediol, 1,11-
undecanediol and 1,12-dodecanediol. As specific
polyols there may be mentioned polyhydric alcohols such
25 as trimethylolethane, trimethylolpropane,
trimethylolbutane, di-(trimethylolpropane), tri-

(trimethylolpropane), pentaerythritol, di-
(pentaerythritol), tri-(pentaerythritol), glycerin,
polyglycerin (2-20mers of glycerin), 1,3,5-pentanetriol,
sorbitol, sorbitan, sorbitol glycerin condensate,
5 adonitol, arabitol, xylitol and mannitol, sugars such
as xylose, arabinose, ribose, rhamnose, glucose,
fructose, galactose, mannose, sorbose, cellobiose,
maltose, isomaltose, trehalose, sucrose, raffinose,
gentianose and melezitose and their partial etherified
10 products, as well as methylglucoside. Preferred
polyols among these are hindered alcohols such as
neopentyl glycol, trimethylolethane, trimethylolpropane,
trimethylolbutane, di-(trimethylolpropane), tri-
(trimethylolpropane), pentaerythritol, di-
15 (pentaerythritol) and tri-(pentaerythritol).

[0045] There are no particular restrictions on the
number of carbon atoms in the fatty acid used in the
polyol ester, but ordinarily a C1-24 fatty acid will be
used. Among C1-24 fatty acids, from the standpoint of
20 lubricity, those having 3 or more carbon atoms are
preferred, those having 4 or more carbon atoms are more
preferred, those having 5 or more carbon atoms are even
more preferred, and those having 10 or more carbon
atoms are especially preferred. From the standpoint of
25 miscibility with refrigerants, those with no greater
than 18 carbon atoms are preferred, those with no

greater than 12 carbon atoms are more preferred, and those with no greater than 9 carbon atoms are even more preferred.

[0046] Such fatty acids may be either straight-chain fatty acids or branched fatty acids, but straight-chain fatty acids are preferred from the standpoint of lubricity, while branched fatty acids are preferred from the standpoint of hydrolytic stability. The fatty acids may be either saturated fatty acids or unsaturated fatty acids.

[0047] As specific fatty acids there may be mentioned pentanoic acid, hexanoic acid, heptanoic acid, octanoic acid, nonanoic acid, decanoic acid, undecanoic acid, dodecanoic acid, tridecanoic acid, tetradecanoic acid, pentadecanoic acid, hexadecanoic acid, heptadecanoic acid, octadecanoic acid, nonadecanoic acid, eicosanoic acid and oleic acid, and the fatty acids may be either straight-chain fatty acids or branched fatty acids, and may also be fatty acids wherein the α -carbon atom is a quaternary carbon atom (neo acids). Preferred for use among these are valeric acid (n-pentanoic acid), caproic acid (n-hexanoic acid), enanthic acid (n-heptanoic acid), caprylic acid (n-octanoic acid), pelargonic acid (n-nonanoic acid), capric acid (n-decanoic acid), oleic acid (cis-9-octadecenoic acid), isopentanoic acid (3-methylbutanoic

acid), 2-methylhexanoic acid, 2-ethylpentanoic acid, 2-ethylhexanoic acid and 3,5,5-trimethylhexanoic acid.

[0048] A polyol ester used for the invention may be a partial ester wherein a portion of the hydroxyl groups of the polyol remain unesterified, so long as it has at least two ester groups, or it may be a complete ester wherein all of the hydroxyl groups are esterified, or even a mixture of a partial ester and a complete ester, but complete esters are preferred.

[0049] Complex esters are esters of fatty acids and dibasic acids with monohydric alcohols and polyols, and such fatty acids, dibasic acids, monohydric alcohols and polyols used may be the same fatty acids, dibasic acids, monohydric alcohols and polyols mentioned above for the dibasic acid ester and polyol ester.

[0050] A carbonic acid ester is a compound having a carbonic acid ester bond represented by the following formula (1) in the molecule:



The number of carbonic acid ester bonds represented by formula (1) may be one, two or more per molecule.

[0052] As alcohols forming the carbonic acid ester there may be used monohydric alcohols and polyols mentioned above for dibasic acid esters and polyol esters, as well as polyglycols and polyglycol-added polyols. There may also be used compounds obtained

from carbonic acid and fatty acids and/or dibasic acids.

[0053] Needless to mention, when an ester is used, one compound with a specific structure may be used alone, or two or more compounds with different structures may be used in combination.

[0054] Among the esters mentioned above, dibasic acid esters, polyol esters and carbonic acid esters are preferred from the standpoint of excellent miscibility with refrigerants.

[0055] More preferred among dibasic acid esters are alicyclic dicarboxylic acid esters such as 1,2-cyclohexanedicarboxylic acid and 4-cyclohexene-1,2-dicarboxylic acid, from the standpoint of miscibility with refrigerants and thermal/hydrolytic stability.

[0056] As specific examples of dibasic acid esters which are preferably used for the invention, there may be mentioned dibasic acid esters obtained from one or more monohydric alcohols selected from the group consisting of butanol, pentanol, hexanol, heptanol, octanol and nonanol, and one or more dibasic acids selected from the group consisting of 1,2-cyclohexanedicarboxylic acid and 4-cyclohexene-1,2-dicarboxylic acid, as well as mixtures thereof.

[0057] Two or more different monohydric alcohols are preferably used to form a dibasic acid ester according to the invention, as this will tend to improve the low

temperature property and refrigerant miscibility of the refrigerating machine oil composition. Dibasic acid esters composed of two or more monohydric alcohols include mixtures of two or more different esters of a
5 dibasic acid and one type of alcohol, and esters of a dibasic acid and two or more different mixed alcohols.


[0058] More preferred among polyol esters for their excellent hydrolytic stability are esters of hindered alcohols such as neopentyl glycol, trimethylolethane,
10 trimethylolpropane, trimethylolbutane, di-(trimethylolpropane), tri-(trimethylolpropane), pentaerythritol and di-(pentaerythritol) and tri-(pentaerythritol), with esters of neopentyl glycol, trimethylolethane, trimethylolpropane,
15 trimethylolbutane and pentaerythritol being more preferred, and esters of pentaerythritol being most preferred for their excellent refrigerant stability and hydrolytic stability.

[0059] As specific examples of polyol esters
20 preferred used according to the invention there may be mentioned diesters, triesters and tetraesters obtained from one or more types of fatty acids selected from the group consisting of valeric acid, caproic acid, enanthic acid, caprylic acid, pelargonic acid, capric
25 acid, oleic acid, isopentanoic acid, 2-methylhexanoic acid, 2-ethylpentanoic acid, 2-ethylhexanoic acid and


3,5,5-trimethylhexanoic acid, and one or more types of alcohols selected from the group consisting of neopentyl glycol, trimethylolethane, trimethylolpropane, trimethylolbutane and pentaerythritol, as well as mixtures thereof.

[0060] Two or more different fatty acids preferably form the polyol ester according to the invention, as this will tend to improve the low temperature property and refrigerant miscibility of the refrigerating machine oil composition. Polyol esters composed of two or more fatty acids include mixtures of two or more different esters of a polyol and one type of fatty acid, and esters of a polyol and two or more different mixed fatty acids.

[0061] Preferred among carbonic acid esters are those having the structure represented by the following general formula (2):



[wherein X^1 is hydrogen, alkyl, cycloalkyl or a group represented by the following general formula (3):



(wherein Y^2 represents hydrogen, alkyl or cycloalkyl, A^3 represents C2-4 alkylene, and e represents an integer of 1-50), A^1 and A^2 may be the same or different and each represents C2-4 alkylene, Y^1 represents hydrogen, alkyl or cycloalkyl, B represents the residue of a

compound having 3-20 hydroxyl groups, a represents 1-20, b represents 0-19 (a+b representing an integer of 3-20), c represents an integer of 0-50, and d represents an integer of 1-50]

5 [0063] In formula (2) above, X^1 represents hydrogen, alkyl, cycloalkyl or a group represented by formula (3) above. The number of carbon atoms of the alkyl group here is not particularly restricted, but will normally be 1-24, preferably 1-18 and more preferably 1-12. The
10 alkyl group may be either straight-chain or branched.
[0064] As specific C1-24 alkyl groups there may be mentioned methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, straight-chain or branched pentyl, straight-chain or branched hexyl,
15 straight-chain or branched heptyl, straight-chain or branched octyl, straight-chain or branched nonyl, straight-chain or branched decyl, straight-chain or branched undecyl, straight-chain or branched dodecyl, straight-chain or branched tridecyl, straight-chain or
20 branched tetradecyl, straight-chain or branched pentadecyl, straight-chain or branched hexadecyl, straight-chain or branched heptadecyl, straight-chain or branched octadecyl, straight-chain or branched nonadecyl, straight-chain or branched eicosyl,
25 straight-chain or branched heneicosyl, straight-chain or branched docosyl, straight-chain or branched

tricosyl and straight-chain or branched tetracosyl.

[0065] As specific cycloalkyl groups there may be mentioned cyclopentyl, cyclohexyl and cycloheptyl.

[0066] As C2-4 alkylene groups represented by A^3 in formula (2) above there may be mentioned specifically ethylene, propylene, trimethylene, butylene, tetramethylene, 1-methyltrimethylene, 2-methyltrimethylene, 1,1-dimethylethylene and 1,2-dimethylethylene.

[0067] Y^2 in formula (2) above represents hydrogen, alkyl or cycloalkyl. The number of carbon atoms of the alkyl group here is not particularly restricted, but will normally be 1-24, preferably 1-18 and more preferably 1-12. The alkyl group may be either straight-chain or branched. As C1-24 alkyl groups there may be mentioned the alkyl groups mentioned above for X^1 .

[0068] As specific examples of cycloalkyl groups there may be mentioned cyclopentyl, cyclohexyl and cycloheptyl.

[0069] Among the groups represented by Y^2 there are preferred hydrogen and C1-12 alkyl, with hydrogen, methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, sec-butyl, tert-butyl, n-pentyl, iso-pentyl, neo-pentyl, n-hexyl, iso-hexyl, n-heptyl, iso-heptyl, n-octyl, iso-octyl, n-nonyl, iso-nonyl, n-decyl, iso-decyl, n-

undecyl, iso-undecyl, n-dodecyl or iso-dodecyl being more preferred. Also, e represents an integer of 1-50.

[0070] As groups represented by X^1 there are preferred hydrogen, C1-12 alkyl or groups represented by general formula (3) above, with hydrogen, methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, sec-butyl, tert-butyl, n-pentyl, iso-pentyl, neo-pentyl, n-hexyl, iso-hexyl, n-heptyl, iso-heptyl, n-octyl, iso-octyl, n-nonyl, iso-nonyl, n-decyl, iso-decyl, n-undecyl, iso-undecyl, n-dodecyl, iso-dodecyl or groups represented by general formula (3) being more preferred.

[0071] As specific compounds having B as a residue and containing 3-20 hydroxyl groups there may be mentioned the polyols referred to above.

[0072] A^1 and A^2 may be the same or different and each represents a C2-4 alkylene group. As specific alkylene groups there may be mentioned ethylene, propylene, trimethylene, butylene, tetramethylene, 1-methyltrimethylene, 2-methyltrimethylene, 1,1-dimethylethylene and 1,2-dimethylethylene.

[0073] Y^1 represents hydrogen, alkyl or cycloalkyl. The number of carbon atoms of the alkyl group here is not particularly restricted, but will normally be 1-24, preferably 1-18 and more preferably 1-12. The alkyl group may be either straight-chain or branched. As C1-24 alkyl groups there may be mentioned the alkyl groups

mentioned above for X^1 .

[0074] As specific cycloalkyl groups, there may be mentioned cyclopentyl, cyclohexyl and cycloheptyl.

5 [0075] Among the groups represented by Y^1 there are preferred hydrogen and C1-12 alkyl, with hydrogen, methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, sec-butyl, tert-butyl, n-pentyl, iso-pentyl, neo-pentyl, n-hexyl, iso-hexyl, n-heptyl, iso-heptyl, n-octyl, iso-octyl, n-nonyl, iso-nonyl, n-decyl, iso-decyl, n-undecyl, iso-undecyl, n-dodecyl or iso-dodecyl being
10 more preferred.

[0076] In formulas (2) and (3) above, c, d and e represent the polymerization degree of the polyoxyalkylene chain, and the polyoxyalkylene chains
15 in the molecule may be the same or different. When the carbonic acid ester represented by formula (2) has different polyoxyalkylene chains, there are no particular restrictions on the form of polymerization of the oxyalkylene groups, and they may be randomly
20 copolymerized or block copolymerized.

[0077] The carbonic acid ester used for the invention may be obtained by any production process, and for example, it may be obtained by addition of an alkylene oxide to a polyol compound to produce a
25 polyalkyleneglycol polyolether, and then reacting this with a chloroformate at 0-30°C in the presence of an


alkali, e.g. an alkali metal hydroxide such as sodium hydroxide or potassium hydroxide, an alkali metal alkoxide such as sodium methoxide or sodium ethoxide, or metallic sodium. Alternatively, it may be obtained
5 by reacting a polyalkyleneglycol polyolether with a carbonic acid source such as a carbonic acid diester or phosgene, at 80-150°C in the presence of an alkali, e.g. an alkali metal hydroxide such as sodium hydroxide or potassium hydroxide, an alkali metal alkoxide such as
10 sodium methoxide or sodium ethoxide, or metallic sodium. If necessary, the free hydroxyl groups may then be etherified.

[0078] The product obtained from the aforementioned starting materials may be purified to remove by-
15 products or unreacted substances, but there is no problem with the presence of small amounts of by-products or unreacted substances so long as they do not inhibit the excellent performance of the lubricating oil of the invention.

[0079] When a carbonic acid ester according to the
20 invention is used, one compound with a specific structure may be used alone, or two or more compounds with different structures may be used in combination. The molecular weight of the carbonic acid ester of the
25 invention is not particularly restricted, but from the standpoint of further improving the seal property of

the compressor, the number average molecular weight is preferably 200-4000 and more preferably 300-3000. The kinematic viscosity of the carbonic acid ester of the invention at 100°C is preferably 2-150 mm²/s and more preferably 4-100 mm²/s.

[0080] As examples of polyoxyalkylene glycols to be used in the lubricating oil of the invention there may be mentioned compounds represented by the following general formula (4):



[wherein R¹ represents hydrogen, C1-10 alkyl, C2-10 acyl or the residue of a compound having 2-8 hydroxyl groups, R² represents C2-4 alkylene, R³ represents hydrogen, C1-10 alkyl or C2-10 acyl, f represents an integer of 1-80, and g represents an integer of 1-8].

[0082] In general formula (4), the alkyl groups represented by R¹ and R³ may be straight-chain, branched or cyclic. As specific examples of alkyl groups there may be mentioned methyl, ethyl, n-propyl, isopropyl, straight-chain or branched butyl, straight-chain or branched pentyl, straight-chain or branched hexyl, straight-chain or branched heptyl, straight-chain or branched octyl, straight-chain or branched nonyl, straight-chain or branched decyl, cyclopentyl and cyclohexyl. If the alkyl group contains more than 10 carbon atoms, the refrigerant miscibility will be

reduced and phase separation will tend to occur. The preferred number of carbon atoms in the alkyl group is 1-6.

[0083] The alkyl group portion of an acyl group represented by R^1 and R^3 may be straight-chain, branched or cyclic. As specific examples of alkyl portions for acyl groups there may be mentioned the C1-9 alkyl groups among those mentioned above as examples of alkyl groups. If the acyl group contains more than 10 carbon atoms, the refrigerant miscibility will be reduced and phase separation may occur. The preferred number of carbon atoms in the acyl group is 2-6.

[0084] When the groups represented by R^1 and R^3 are both alkyl, or when they are both acyl, the groups represented by R^1 and R^3 may be the same or different. Also, when g is 2 or greater, the groups represented by R^1 and R^3 in the same molecule may be the same or different.

[0085] When the group represented by R^1 is the residue of a compound having 2-8 hydroxyl groups, the compound may be either linear or cyclic. As specific compounds with two hydroxyl groups there may be mentioned ethylene glycol, 1,3-propanediol, propylene glycol, 1,4-butanediol, 1,2-butanediol, 2-methyl-1,3-propanediol, 1,5-pentanediol, neopentyl glycol, 1,6-hexanediol, 2-ethyl-2-methyl-1,3-propanediol, 1,7-

heptanediol, 2-methyl-2-propyl-1,3-propanediol, 2,2-diethyl-1,3-propanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,11-undecanediol and 1,12-dodecanediol.

5 [0086] As specific compounds with 3-8 hydroxyl groups there may be mentioned polyhydric alcohols such as trimethylolethane, trimethylolpropane, trimethylolbutane, di-(trimethylolpropane), tri-(trimethylolpropane), pentaerythritol, di-(pentaerythritol), tri-(pentaerythritol), glycerin, 10 polyglycerin (2-6mers of glycerin), 1,3,5-pentanetriol, sorbitol, sorbitan, sorbitol glycerin condensate, adonitol, arabitol, xylitol and mannitol, sugars such as xylose, arabinose, ribose, rhamnose, glucose, 15 fructose, galactose, mannose, sorbose, cellobiose, maltose, isomaltose, trehalose, sucrose, raffinose, gentianose and melezitose, as well as their partial etherified products, and methylglucoside.

20 [0087] Among the polyoxyalkylene glycols represented by general formula (4) above, there are preferred those wherein at least one of R^1 and R^3 is an alkyl group (more preferably a C-14 alkyl group), and especially methyl, from the standpoint of refrigerant miscibility. From the standpoint of thermal and chemical stability, 25 R^1 and R^3 are both preferably alkyl groups (more preferably C1-4 alkyl groups), and most preferably both

are methyl. From the standpoint of production ease and cost, preferably at least one of R^1 and R^3 is an alkyl group (more preferably a C1-4 alkyl group) and the other is hydrogen, and most preferably one is methyl and the other is hydrogen.

[0088] R^2 in general formula (4) above represents C2-4 alkylene, and as specific alkylene groups there may be mentioned ethylene, propylene and butylene. As oxyalkylene groups for the repeating unit represented by OR^2 there may be mentioned oxyethylene, oxypropylene and oxybutylene. The oxyalkylene groups in the same molecule may be the same, or the molecule may contain two or more different oxyalkylene groups.

[0089] Among the polyoxyalkylene glycols represented by general formula (4), copolymers comprising oxyethylene (EO) and oxypropylene (PO) are preferred from the standpoint of refrigerant miscibility and viscosity-temperature properties, in which case the proportion of oxyethylene in the total of the oxyethylene and oxypropylene ($EO/(PO+EO)$) is preferably in the range of 0.1-0.8, and more preferably in the range of 0.3-0.6, from the standpoint of seizure load and viscosity-temperature properties.


[0090] From the standpoint of hygroscopicity and thermal-oxidative stability, the value of $EO/(PO+EO)$ is preferably in the range of 0-0.5, more preferably in

the range of 0-0.2 and most preferably zero (i.e. a propylene oxide homopolymer).

[0091] In general formula (4) above, f represents an integer of 1-80, and g represents an integer of 1-8. When R⁷ is alkyl or acyl, for example, g is 1. When R⁷ is the residue of a compound with 2-8 hydroxyl groups, g is the number of hydroxyl groups in the compound.


[0092] There are no particular restrictions on the product of f and g (f x g), but the average value of f x g is preferably 6-80 in order to provide a satisfactory balance for the required performance as a refrigerating machine lubricating oil.

[0093] Among polyoxyalkylene glycols having the structure described above, polyoxypropyleneglycol dimethyl ether represented by the following general formula (5):



(wherein h represents an integer of 6-80)


and polyoxyethylenepolyoxypropyleneglycol dimethyl ether represented by the following general formula (6):



(wherein i and j are each 1 or greater and the total of i and j is 6-80)


are preferred from the standpoint of economy and the effect described above, while polyoxypropyleneglycol monobutyl ether represented by the following general

formula (7):




(wherein k represents an integer of 6-80),

polyoxypropyleneglycol monomethyl ether represented by
5 the following general formula (8):




(wherein 1 represents an integer of 6-80),

polyoxyethylenepolyoxypropyleneglycol monomethyl ether
represented by the following general formula (9):




(wherein m and n are each 1 or greater and the total of
m and n is 6-80),

polyoxyethylenepolyoxypropyleneglycol monobutyl ether
represented by the following general formula (10):



(wherein m and n are each 1 or greater and the total of
m and n is 6-80), and

polyoxypropylene glycol diacetate represented by the
following general formula (11):




(wherein 1 represents an integer of 6-80)

are preferred from the standpoint of economy.


[0101] As the aforementioned polyoxyalkylene glycols
of the invention, there may be used polyoxyalkylene
25 glycol derivatives comprising at least one structural
unit represented by general formula (12):

[Chemical Formula 1]



[wherein R⁴-R⁷ may be the same or different and each represents hydrogen, a C1-10 monovalent hydrocarbon group or a group represented by the following general formula (13):

[Chemical Formula 2]



(wherein R⁸ and R⁹ may be the same or different and each represents hydrogen, a C1-10 monovalent hydrocarbon group or C2-20 alkoxyalkyl, R¹⁰ represents C2-5 alkylene, substituted alkylene having alkyl as a substituent and comprising a total of 2-5 carbon atoms, or substituted alkylene having alkoxyalkyl as a substituent and comprising 4-10 carbon atoms, r represents an integer of 0-20, and R¹¹ represents a C1-10 monovalent hydrocarbon group), and at least one from among R⁸-R¹¹ is a group represented by general formula (13)].

[0102] In formula (12) above, R⁴-R⁷ each represents

hydrogen, a C1-10 monovalent hydrocarbon group or a group represented by general formula (13) above, and as specific C1-10 monovalent hydrocarbon groups there may be mentioned C1-10 straight-chain or branched alkyl, C2-10 straight-chain or branched alkenyl, C5-10 cycloalkyl or alkylcycloalkyl, C6-10 aryl or alkylaryl and C7-10 arylalkyl. Preferred among these monovalent hydrocarbon groups are $\leq C6$ monovalent hydrocarbon groups, and especially $\leq C3$ alkyl, with methyl, ethyl, n-propyl and isopropyl being specifically preferred.

[0103] In general formula (13) above, R^8 and R^9 each represent hydrogen, a C1-10 monovalent hydrocarbon group or C2-20 alkoxyalkyl, among which $\leq C3$ alkyl and $\leq C6$ alkoxyalkyl groups are preferred. As specific $\leq C3$ alkyl groups there may be mentioned methyl, ethyl, n-propyl and isopropyl. As specific C2-6 alkoxyalkyl groups there may be mentioned methoxymethyl, ethoxymethyl, n-propoxymethyl, isopropoxymethyl, n-butoxymethyl, isobutoxymethyl, sec-butoxymethyl, tert-butoxymethyl, pentoxymethyl (including all isomers thereof), methoxyethyl (including all isomers thereof), ethoxyethyl (including all isomers thereof), propoxyethyl (including all isomers thereof), butoxyethyl (including all isomers thereof), methoxypropyl (including all isomers thereof), ethoxypropyl (including all isomers thereof),

propoxypropyl (including all isomers thereof),
 methoxybutyl (including all isomers thereof),
 ethoxybutyl (including all isomers thereof) and
 methoxypentyl (including all isomers thereof).

5 [0104] In general formula (13) above, R^{10} represents
 C2-5 alkylene, substituted alkylene having alkyl as a
 substituent and comprising a total of 2-5 carbon atoms,
 or substituted alkylene having alkoxyalkyl as a
 substituent and comprising 4-10 carbon atoms, and
 10 preferably it represents C2-4 alkylene or substituted
 ethylene having a total of no more than 6 carbon atoms.
 As specific C2-4 alkylene groups there may be mentioned
 ethylene, propylene, butylene. As specific substituted
 ethylene groups having a total of no more than 6 carbon
 15 atoms there may be mentioned 1-(methoxymethyl)ethylene,
 2-(methoxymethyl)ethylene, 1-(methoxyethyl)ethylene, 2-
 (methoxyethyl)ethylene, 1-(ethoxymethyl)ethylene, 2-
 (ethoxymethyl)ethylene, 1-methoxymethyl-2-
 methylethylene, 1,1-bis(methoxymethyl)ethylene, 2,2-
 20 bis(methoxymethyl)ethylene, 1,2-
 bis(methoxymethyl)ethylene, 1-methyl-2-
 methoxymethylethylene, 1-methoxymethyl-2-methylethylene,
 1-ethyl-2-methoxymethylethylene, 1-methoxymethyl-2-
 ethylethylene, 1-methyl-2-ethoxymethylethylene, 1-
 25 ethoxymethyl-2-methylethylene, 1-methyl-2-
 methoxyethylethylene and 1-methoxyethyl-2-

methylethylene.


[0105] In general formula (13), R^{11} represents a C1-10 monovalent hydrocarbon group, and as such hydrocarbon groups there may be mentioned specifically C1-10 straight-chain or branched alkyl, C2-10 straight-chain or branched alkenyl, C5-10 cycloalkyl or alkylcycloalkyl, C6-10 aryl or alkylaryl and C7-10 arylalkyl. Preferred among these are $\leq C6$ monovalent hydrocarbon groups and especially $\leq C3$ alkyl groups, with methyl, ethyl, n-propyl and isopropyl being specifically preferred.

[0106] In general formula (12), at least one from among R^4 - R^7 is a group represented by general formula (13) above. In particular, preferably either R^4 or R^6 is a group represented by general formula (13) and the other R^4 or R^6 , as well as R^5 and R^7 , is each hydrogen or a C1-10 monovalent hydrocarbon group.

[0107] Polyoxyalkylene glycols having a structural unit represented by general formula (12) above which are preferred for use according to the invention may be largely classified into three types: homopolymers comprising a structural unit represented by general formula (12); copolymers comprising two or more structural units represented by general formula (12) and having different structures; and copolymers comprising a structural unit represented by general

formula (12) and another structural unit, for example, a structural unit represented by the following general formula (14):

[Chemical Formula 3]




[wherein R^{12} - R^{15} may be the same or different and each represents hydrogen or C1-3 alkyl].

As preferred examples of the aforementioned homopolymers there may be mentioned homopolymers having 1-200 structural units A represented by general formula (12) and comprising hydroxyl, C1-10 acyloxy, C1-10 alkoxy or aryloxy groups as terminal groups. As preferred examples of copolymers there may be mentioned copolymers having 1-200 each of two different structural units A and B represented by general formula (12), or having 1-200 structural units A represented by general formula (12) and 1-200 structural units C represented by general formula (12), and comprising hydroxyl, C1-10 acyloxy, C1-10 alkoxy or aryloxy groups as terminal groups. Such copolymers may have a polymerization form of alternating copolymerization, random copolymerization or block copolymerization of structural unit A and structural unit B (or structural

unit C), or may be graft copolymers of structural unit B grafted onto a main chain of structural unit A.

[0108] As examples of polyvinyl ethers to be used for the invention there may be mentioned polyvinyl ether-based compounds having a structural unit represented by the following general formula (15):


[Chemical Formula 4]



[wherein R^{16} - R^{18} may be the same or different and each represents hydrogen or a C1-8 hydrocarbon group, R^{19} represents a C1-10 divalent hydrocarbon group or C2-20 divalent ether-bonded oxygen-containing hydrocarbon group, R^{20} represents a C1-20 hydrocarbon group, s represents an integer whose average is 0-10, R^{16} - R^{20} may be the same or different for each structural unit, and when the structural unit represented by general formula (15) has multiple R^{19}O groups, the multiple R^{19}O groups may be the same or different].

[0109] There may also be used polyvinyl ether-based compounds comprising block copolymers or random copolymers having a structural unit represented by general formula (15) above and a structural unit represented by the following general formula (16):

[Chemical Formula 5]



[wherein R^{21} - R^{24} may be the same or different and each represents hydrogen or a C1-20 hydrocarbon group, and R^{21} - R^{24} may be the same or different for each structural unit].

[0110] R^{16} - R^{18} in general formula (15) above each represents hydrogen or a C1-8 hydrocarbon group (preferably a C1-4 hydrocarbon group), and they may be the same or different. As specific hydrocarbon groups there may be mentioned alkyl groups such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl isomers, hexyl isomers, heptyl isomers and octyl isomers; cycloalkyl groups such as cyclopentyl, cyclohexyl, methylcyclohexyl isomers, ethylcyclohexyl isomers and dimethylcyclohexyl isomers; aryl groups such as phenyl, methylphenyl isomers, ethylphenyl isomers and dimethylphenyl isomers; and arylalkyl groups such as benzyl, phenylethyl isomers and methylbenzyl isomers; however, hydrogen is preferred for R^{22} - R^{24} .

[0111] R^{19} in general formula (15) represents a C1-10 (preferably C2-10) divalent hydrocarbon group or a C2-

20 divalent ether-bonded oxygen-containing hydrocarbon group. As specific C1-10 divalent hydrocarbon groups there may be mentioned divalent aliphatic linear hydrocarbon groups such as methylene, ethylene, phenylethylene, 1,2-propylene, 2-phenyl-1,2-propylene, 1,3-propylene, butylene isomers, pentylene isomers, hexylene isomers, heptylene isomers, octylene isomers, nonylene isomers and decylene isomers; alicyclic hydrocarbon groups having two binding sites in the alicyclic hydrocarbon group, such as cyclohexane, methylcyclohexane, ethylcyclohexane, dimethylcyclohexane and propylcyclohexane; divalent aromatic hydrocarbon groups such as phenylene isomers, methylphenylene isomers, ethylphenylene isomers, dimethylphenylene isomers and naphthylene isomers; alkylaromatic hydrocarbon groups having a monovalent binding site at the alkyl group portion and the aromatic portion of the alkylaromatic hydrocarbon, such as toluene, xylene and ethylbenzene; alkylaromatic hydrocarbon groups having a binding site at the alkyl portion of the polyalkylaromatic hydrocarbon, such as xylene and diethylbenzene. Particularly preferred among these are C2-4 aliphatic linear hydrocarbon groups.

[0112] As examples of preferred C2-20 divalent ether-bonded oxygen-containing hydrocarbon groups there

may be mentioned specifically methoxymethylene,
methoxyethylene, methoxymethylethylene, 1,1-
bismethoxymethylethylene, 1,2-bismethoxymethylethylene,
ethoxymethylethylene, (2-methoxyethoxy)methylethylene
5 and (1-methyl-2-methoxy)methylethylene. The letter s
in general formula (15) represents the number of
repeats of $R^{19}O$, and its average is in the range of 0-10,
and preferably 0-5. When multiple $R^{19}O$ groups are
present in the same structural unit, the multiple $R^{19}O$
10 groups may be the same or different.

[0113] R^{20} in general formula (15) represents a C1-20
and preferably C1-10 hydrocarbon group, and as such
hydrocarbon groups there may be mentioned specifically
alkyl groups such as methyl, ethyl, n-propyl, isopropyl,
15 n-butyl, isobutyl, sec-butyl, tert-butyl, pentyl
isomers, hexyl isomers, heptyl isomers, octyl isomers,
nonyl isomers and decyl isomers; cycloalkyl groups such
as cyclopentyl, cyclohexyl, methylcyclohexyl isomers,
ethylcyclohexyl isomers, propylcyclohexyl isomers and
20 dimethylcyclohexyl isomers; aryl groups such as phenyl,
methylphenyl isomers, ethylphenyl isomers,
dimethylphenyl isomers, propylphenyl isomers,
trimethylphenyl isomers, butylphenyl isomers and
naphthyl isomers; and arylalkyl groups such as benzyl,
25 phenylethyl isomers, methylbenzyl isomers, phenylpropyl
isomers and phenylbutyl isomers. $R^{22}-R^{26}$ may be the same

or different for each structural unit.

5 [0114] When a polyvinyl ether used for the invention is a homopolymer comprising a structural unit represented by general formula (15) above, the carbon/oxygen molar ratio is preferably in the range of 4.2-7.0. A molar ratio of less than 4.2 will produce excessive hygroscopicity, while a molar ratio of 7.0 will tend to reduce miscibility with refrigerants.

10 [0115] In general formula (16) above, R^{21} - R^{24} may be the same or different and each represents hydrogen or a C1-20 hydrocarbon group. As C1-20 hydrocarbon groups there may be mentioned the hydrocarbon groups for R^{20} in general formula (15). R^{21} - R^{24} may be the same or different for each structural unit.


15 [0116] When a polyvinyl ether used for the invention is a block copolymer or random copolymer of a structural unit represented by general formula (15) and a structural unit represented by general formula (16), the carbon/oxygen molar ratio is preferably in the range of 4.2-7.0. A molar ratio of less than 4.2 will produce excessive hygroscopicity, while a molar ratio of 7.0 will tend to reduce miscibility with refrigerants.

20 [0117] According to the invention, there may also be used a mixture of a homopolymer comprising a structural unit represented by general formula (15) with a block

copolymer or random copolymer comprising a structural unit represented by general formula (15) and a structural unit represented by general formula (16). Such homopolymers and copolymers may be produced, respectively, by polymerization of the corresponding vinyl ether-based monomer, and copolymerization of the corresponding hydrocarbon monomer having an olefinic double bond and the corresponding vinyl ether-based monomer.

[0118] As polyvinyl ethers to be used for the invention there are preferred those wherein at least one of the terminal structures is represented by the following general formula (17) or (18):


[Chemical Formula 6]



[wherein R^{25} - R^{27} may be the same or different and each represents hydrogen or a C1-8 hydrocarbon group, R^{28} represents a C1-10 divalent hydrocarbon group or a C2-20 divalent ether-bonded oxygen-containing hydrocarbon group, R^{29} represents a C1-20 hydrocarbon group and t represents a number whose average is 0-10, with the proviso that when the terminal structure represented by general formula (17) contains multiple R^{28}O groups, the

multiple $R^{28}O$ groups may be the same or different]

[Chemical Formula 7]




[wherein $R^{30}-R^{31}$ may be the same or different and each

5 represents hydrogen or a C1-20 hydrocarbon group]

and the other terminal structure is represented by the following general formula (19) or (20):


[Chemical Formula 8]



10 [wherein $R^{34}-R^{36}$ may be the same or different and each represents hydrogen or a C1-8 hydrocarbon group, R^{37} represents a C1-10 divalent hydrocarbon group or a C2-20 divalent ether-bonded oxygen-containing hydrocarbon group, R^{38} represents a C1-20 hydrocarbon group and t

15 represents a number whose average is 0-10, with the proviso that when the terminal structure represented by general formula (19) contains multiple $R^{37}O$ groups, the multiple $R^{37}O$ groups may be the same or different]


[Chemical Formula 9]



[wherein R^{39} - R^{42} may be the same or different and each represents hydrogen or a C1-20 hydrocarbon group];

5 and those wherein one of the terminal structures is represented by general formula (17) or (18) and the other is represented by the following general formula (21):

[Chemical Formula 10]



10 [wherein R^{43} - R^{45} may be the same or different and each represents hydrogen or a C1-8 hydrocarbon group].
Among such polyvinyl ethers, the following may be mentioned as particularly preferable.

15 (1) Polyvinyl ethers wherein one terminal has a structure represented by general formula (17) or (18) and the other has a structure represented by general formula (19) or (20), any of R^{16} - R^{18} in general formula (15) is hydrogen, s is an integer of 0-4, R^{19} is a C2-4 divalent hydrocarbon group, and R^{20} is a C1-20
20 hydrocarbon group;

(2) Polyvinyl ethers having only a structural unit represented by general formula (15), wherein one terminal has a structure represented by general formula (17) and the other has a structure represented by general formula (18), any of R^{16} - R^{18} in general formula (15) is hydrogen, s is an integer of 0-4, R^{19} is a C2-4 divalent hydrocarbon group, and R^{20} is a C1-20 hydrocarbon group;

(3) Polyvinyl ethers wherein one terminal has a structure represented by general formula (17) or (18) and the other has a structure represented by general formula (19), any of R^{16} - R^{18} in general formula (15) is hydrogen, s is an integer of 0-4, R^{19} is a C2-4 divalent hydrocarbon group, and R^{20} is a C1-20 hydrocarbon group;


and

(4) Polyvinyl ethers having only a structural unit represented by general formula (15), wherein one terminal has a structure represented by general formula (17) and the other has a structure represented by general formula (20), any of R^{16} - R^{18} in general formula (15) is hydrogen, s is an integer of 0-4, R^{19} is a C2-4 divalent hydrocarbon group, and R^{20} is a C1-20 hydrocarbon group.

[0119] According to the invention, there may also be used polyvinyl ethers having a structural unit represented by general formula (15), wherein one

terminal has a structure represented by general formula (17) and the other has a structure represented by the following general formula (22):


[Chemical Formula 11]



[wherein R⁴⁶-R⁴⁸ may be the same or different and each represents hydrogen or a C1-8 hydrocarbon group, R⁴⁹ and R⁵¹ may be the same or different and each represents a C2-10 divalent hydrocarbon group, R⁵⁰ and R⁵² may be the same or different and each represents a C1-10 hydrocarbon group, u and v may be the same or different and each represents a number whose average is 0-10, and when the terminal structure represented by general formula (22) has multiple R⁴⁹O or R⁵¹O groups, the multiple R⁴⁹O or R⁵¹O groups may be the same or different].

[0120] According to the invention, there may also be used polyvinylether-based compounds comprising an alkylvinyl ether homopolymer or copolymer composed of a structural unit represented by the following general formula (23) or (24):

[Chemical Formula 12]



[wherein R^{53} represents a C1-8 hydrocarbon group]

[Chemical Formula 13]




5 [wherein R^{54} represents a C1-8 hydrocarbon group]

and having a weight-average molecular weight of 300-5000, wherein one of the terminals has a structure represented by the following general formula (25) or

(26):

10 [Chemical Formula 14]



[wherein R^{55} represents a C1-3 alkyl group, and R^{56} represents a C1-8 hydrocarbon group]

[Chemical Formula 15]



15 [wherein R^{57} represents a C1-8 hydrocarbon group].

[0121] According to the invention, one oil selected from the group consisting of the aforementioned mineral oils and synthetic oils may be used alone or two or more thereof may be used in combination, but when using
20 an HFC-based refrigerant, polyoxyalkylene glycols, esters, and polyvinyl ethers are preferred among the above-mentioned mineral oils and synthetic oils for


open-type compressors in automobile air conditioners and the like, while alkylbenzenes, esters and polyvinyl ethers are preferred for closed-type compressors in refrigerators, air conditioning machines and the like.

5 [0122] (Phosphorus-based extreme pressure agent)

[0123] The phosphorus-based extreme pressure agent included in the refrigerating machine oil composition of the invention is preferably at least one selected from the group consisting of phosphorothionates (thiophosphoric acid esters), phosphoric acid esters, 10 acidic phosphoric acid esters, acidic phosphoric acid ester amine salts, chlorinated phosphoric acid esters and phosphorous acid esters. Among the aforementioned preferred phosphorus-based extreme pressure agents, 15 phosphorus-based additives other than phosphorothionates include esters of phosphoric acid or phosphorous acid with alkanols and polyether-type alcohols, or their derivatives.

[0124] A phosphorothionate according to the 20 invention is a compound represented by the following general formula (27):

[Chemical Formula 16]



[wherein R^{58} - R^{60} may be the same or different and each represents a C1-24 hydrocarbon group].

[0125] As specific C1-24 hydrocarbon groups represented by R^{58} - R^{60} there may be mentioned alkyl, cycloalkyl, alkenyl, alkylcycloalkyl, aryl, alkylaryl and arylalkyl.

[0126] As examples of alkyl groups there may be mentioned alkyl groups such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl and octadecyl (where these alkyl groups may be either straight-chain or branched).

[0127] As examples of cycloalkyl groups there may be mentioned C5-7 cycloalkyl groups such as cyclopentyl, cyclohexyl and cycloheptyl. As examples of alkylcycloalkyl groups there may be mentioned C6-11 alkylcycloalkyl groups such as methylcyclopentyl, dimethylcyclopentyl, methylethylcyclopentyl, diethylcyclopentyl, methylcyclohexyl, dimethylcyclohexyl, methylethylcyclohexyl, diethylcyclohexyl, methylcycloheptyl, dimethylcycloheptyl, methylethylcycloheptyl and diethylcycloheptyl (where the substituting position of the alkyl group on the cycloalkyl group is optional).

[0128] As examples of alkenyl groups there may be mentioned alkenyl groups such as butenyl, pentenyl,

hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl, dodecenyl, tridecenyl, tetradecenyl, pentadecenyl, hexadecenyl, heptadecenyl and octadecenyl (where the alkyl groups may be either straight-chain or branched, and the position of the double bond is optional).

[0129] As examples of aryl groups there may be mentioned aryl groups such as phenyl and naphthyl. As examples of alkylaryl groups there may be mentioned C7-18 alkylaryl groups such as tolyl, xylyl, ethylphenyl, propylphenyl, butylphenyl, pentylphenyl, hexylphenyl, heptylphenyl, octylphenyl, nonylphenyl, decylphenyl, undecylphenyl and dodecylphenyl (where the alkyl groups may be either straight-chain or branched, and the substituting position on the aryl group is optional).

[0130] As examples of arylalkyl groups there may be mentioned C7-12 arylalkyl groups such as benzyl, phenylethyl, phenylpropyl, phenylbutyl, phenylpentyl and phenylhexyl (where the alkyl groups may be either straight-chain or branched).

[0131] The C1-24 hydrocarbon group represented by $R^{58}-R^{60}$ is preferably alkyl, aryl or alkylaryl, and more preferably C4-18 alkyl, C7-24 alkylaryl or phenyl.

[0132] As specific phosphorothionates represented by general formula (27) there may be mentioned tributyl phosphorothionate, tripentyl phosphorothionate, trihexyl phosphorothionate, triheptyl phosphorothionate,

trioctyl phosphorothionate, trinonyl phosphorothionate,
 tridecyl phosphorothionate, triundecyl
 phosphorothionate, tridodecyl phosphorothionate,
 tritridecyl phosphorothionate, tritetradecyl
 5 phosphorothionate, tripentadecyl phosphorothionate,
 trihexadecyl phosphorothionate, triheptadecyl
 phosphorothionate, trioctadecyl phosphorothionate,
 trioleyl phosphorothionate, triphenyl phosphorothionate,
 tricresyl phosphorothionate, trixylenyl
 10 phosphorothionate, cresyldiphenyl phosphorothionate,
 xylenyldiphenyl phosphorothionate, tris(n-propylphenyl)
 phosphorothionate, tris(isopropylphenyl)
 phosphorothionate, tris(n-butylphenyl)
 phosphorothionate, tris(isobutylphenyl)
 15 phosphorothionate, tris(s-butylphenyl)
 phosphorothionate and tris(t-butylphenyl)
 phosphorothionate. Mixtures of these may also be used.

[0133] There are no particular restrictions on the
 phosphorothionate content, but it will usually be 0.01-
 20 10 wt%, preferably 0.01-5 wt% and more preferably 0.01-
 3 wt% based on the total weight of the refrigerating
 machine oil composition (the total weight of the base
 oil and all additives).

[0134] Among phosphorus-based extreme pressure
 25 agents other than phosphorothionates, the following may
 be mentioned as phosphoric acid esters: tributyl

phosphate, tripentyl phosphate, trihexyl phosphate,
 triheptyl phosphate, trioctyl phosphate, trinonyl
 phosphate, tridecyl phosphate, triundecyl phosphate,
 tridodecyl phosphate, tritridecyl phosphate,
 5 tritetradecyl phosphate, tripentadecyl phosphate,
 trihexadecyl phosphate, triheptadecyl phosphate,
 trioctadecyl phosphate, trioleyl phosphate, triphenyl
 phosphate, tricresyl phosphate, trixylenyl phosphate,
 cresyldiphenyl phosphate and xylenyldiphenyl phosphate;

10 [0135] the following may be mentioned as acidic
 phosphoric acid esters: monobutyl acid phosphate,
 monopentyl acid phosphate, monohexyl acid phosphate,
 monoheptyl acid phosphate, monooctyl acid phosphate,
 monononyl acid phosphate, monodecyl acid phosphate,
 15 monoundecyl acid phosphate, monododecyl acid phosphate,
 monotridecyl acid phosphate, monotetradecyl acid
 phosphate, monopentadecyl acid phosphate, monohexadecyl
 acid phosphate, monoheptadecyl acid phosphate,
 monooctadecyl acid phosphate, monooleyl acid phosphate,
 20 dibutyl acid phosphate, dipentyl acid phosphate,
 dihexyl acid phosphate, diheptyl acid phosphate,
 dioctyl acid phosphate, dinonyl acid phosphate, didecyl
 acid phosphate, diundecyl acid phosphate, didodecyl
 acid phosphate, ditridecyl acid phosphate, ditetradecyl
 25 acid phosphate, dipentadecyl acid phosphate,
 dihexadecyl acid phosphate, diheptadecyl acid phosphate,

dioctadecyl acid phosphate and dioleoyl acid phosphate;

[0136] the following may be mentioned as acidic phosphoric acid ester amine salts: salts of the aforementioned acidic phosphoric acid esters with amines such as methylamine, ethylamine, propylamine, butylamine, pentylamine, hexylamine, heptylamine, octylamine, dimethylamine, diethylamine, dipropylamine, dibutylamine, dipentylamine, dihexylamine, diheptylamine, dioctylamine, trimethylamine, triethylamine, tripropylamine, tributylamine, tripentylamine, trihexylamine, triheptylamine and trioctylamine;

[0137] the following may be mentioned as chlorinated phosphoric acid esters: tris(dichloropropyl) phosphate, tris(chloroethyl) phosphate, tris(chlorophenyl) phosphate and polyoxyalkylene bis[di(chloroalkyl)] phosphate;

[0138] and the following may be mentioned as phosphorous acid esters: dibutyl phosphite, dipentyl phosphite, dihexyl phosphite, diheptyl phosphite, dioctyl phosphite, dinonyl phosphite, didecyl phosphite, diundecyl phosphite, didodecyl phosphite, dioleoyl phosphite, diphenyl phosphite, dicresyl phosphite, tributyl phosphite, tripentyl phosphite, trihexyl phosphite, triheptyl phosphite, trioctyl phosphite, trinonyl phosphite, tridecyl phosphite, triundecyl

phosphite, tridodecyl phosphite, trioleyl phosphite, triphenyl phosphite and tricresyl phosphite. Mixtures of these may also be used.

5 [0139] When a phosphorus-based extreme pressure agent other than a phosphorothionate is included in the refrigerating machine oil composition of the invention, there are no particular restrictions on its content, but the phosphorus-based extreme pressure agent will usually be added in an amount of 0.01-5.0 wt% and
10 preferably 0.02-3.0 wt%, based on the total weight of the refrigerating machine oil composition (the total weight of the base oil and all additives).

[0140] Although any one of the aforementioned phosphorus-based extreme pressure agents alone or any
15 two or more in combination may be used in the refrigerating machine oil composition of the invention, a phosphorothionate is preferably used from the standpoint of achieving more excellent thermal stability.

20 [0141] If a phosphorothionate and a phosphorus-based extreme pressure agent other than a phosphorothionate are used in combination as the phosphorus-based extreme pressure agent, the synergistic effect of the phosphorus-based extreme pressure agents, as well as
25 the synergistic effect of each of the phosphorus-based extreme pressure agents with the oil agent, will

produce a higher degree of the aforementioned effect of the invention, and particularly will further enhance the abrasion resistance.

[0142] (Oil agent)

5 [0143] As oil agents to be used for the invention there may be mentioned ester oil agents, monohydric alcohol oil agents, carboxylic acid oil agents, ether oil agents and the like.

10 [0144] An ester oil agent used may be natural (usually found in a natural fat or oil derived from an animal or plant), or synthetic. According to the invention, synthetic esters are preferred from the standpoint of stability of the resulting refrigerating machine oil composition and homogeneity of the ester component.

15 [0145] A synthetic ester used as the ester oil agent is obtained by reacting an alcohol with a carboxylic acid. The alcohol may be a monohydric alcohol or a polyhydric alcohol. The carboxylic acid may be a monobasic acid or a polybasic acid.

20 [0146] The monohydric alcohol forming the ester oil agent will usually have 1-24, preferably 1-12 and more preferably 1-8 carbon atoms, and such alcohols may be either straight-chain or branched, and either saturated or unsaturated. As specific examples of C1-24 alcohols

25 there may be mentioned methanol, ethanol, straight-

chain or branched propanol, straight-chain or branched butanol, straight-chain or branched pentanol, straight-chain or branched hexanol, straight-chain or branched heptanol, straight-chain or branched octanol, straight-chain or branched nonanol, straight-chain or branched decanol, straight-chain or branched undecanol, straight-chain or branched dodecanol, straight-chain or branched tridecanol, straight-chain or branched tetradecanol, straight-chain or branched pentadecanol, straight-chain or branched hexadecanol, straight-chain or branched heptadecanol, straight-chain or branched octadecanol, straight-chain or branched nonadecanol, straight-chain or branched eicosanol, straight-chain or branched heneicosanol, straight-chain or branched tricosanol, straight-chain or branched tetracosanol, and mixtures thereof.

[0147] A polyhydric alcohol forming the ester oil agent will usually be 2-10 polyhydric and preferably 2-6 polyhydric. As specific examples of 2-10 polyhydric alcohols there may be mentioned dihydric alcohols such as ethylene glycol, diethylene glycol, polyethylene glycol (3-15mers of ethylene glycol), propylene glycol, dipropylene glycol, polypropylene glycol (3-15mers of propylene glycol), 1,3-propanediol, 1,2-propanediol, 1,3-butanediol, 1,4-butanediol, 2-methyl-1,2-propanediol, 2-methyl-1,3-propanediol, 1,2-pentanediol,

1,3-pentanediol, 1,4-pentanediol, 1,5-pentanediol and neopentyl glycol; polyhydric alcohols such as glycerin, polyglycerin (2-8mers of glycerin, such as diglycerin, triglycerin, tetraglycerin, etc.), trimethylolalkanes (trimethylolethane, trimethylolpropane, trimethylolbutane, etc.) and their 2-8mers, pentaerythritol and their 2-4mers, 1,2,4-butanetriol, 1,3,5-pentanetriol, 1,2,6-hexanetriol, 1,2,3,4-butanetetrol, sorbitol, sorbitan, sorbitol glycerin condensate, adonitol, arabitol, xylitol and mannitol; sugars such as xylose, arabinose, ribose, rhamnose, glucose, fructose, galactose, mannose, sorbose, cellobiose, maltose, isomaltose, trehalose and sucrose, and mixtures thereof.

[0148] Among these polyhydric alcohols there are preferred 2-6 polyhydric alcohols such as ethylene glycol, diethylene glycol, polyethylene glycol (3-10mers of ethylene glycol), propylene glycol, dipropylene glycol, polypropylene glycol (3-10mers of propylene glycol), 1,3-propanediol, 2-methyl-1,2-propanediol, 2-methyl-1,3-propanediol, neopentyl glycol, glycerin, diglycerin, triglycerin, trimethylolalkanes (trimethylolethane, trimethylolpropane, trimethylolbutane, etc.) and their 2-4mers, pentaerythritol, dipentaerythritol, 1,2,4-butanetriol, 1,3,5-pentanetriol, 1,2,6-hexanetriol, 1,2,3,4-

butanetetrol, sorbitol, sorbitan, sorbitol glycerin condensate, adonitol, arabitol, xylitol, mannitol, and mixtures thereof. More preferred are ethylene glycol, propylene glycol, neopentyl glycol, glycerin, trimethylolethane, trimethylolpropane, pentaerythritol, sorbitan, and mixtures thereof. Among these, neopentyl glycol, trimethylolethane, trimethylolpropane, pentaerythritol and mixtures thereof are particularly preferred because they provide higher oxidative stability.

[0149] The alcohol forming the ester oil agent of the invention may be a monohydric alcohol or polyhydric alcohol as explained above, but it is preferably a monohydric alcohol from the standpoint of further increasing the abrasion resistance and friction properties when used in combination with the phosphorus-based extreme pressure agent, and from the standpoint of the anti-separation property in a refrigerant atmosphere and at low temperature.

[0150] The acid forming the ester oil agent of the invention may be a monobasic acid, usually C2-24, fatty acid, and such fatty acids may be either straight-chain or branched, and either saturated or unsaturated. As specific examples there may be mentioned saturated fatty acids such as acetic acid, propionic acid, straight-chain or branched butanoic acid, straight-

chain or branched pentanoic acid, straight-chain or
 branched hexanoic acid, straight-chain or branched
 heptanoic acid, straight-chain or branched octanoic
 acid, straight-chain or branched nonanoic acid,
 5 straight-chain or branched decanoic acid, straight-
 chain or branched undecanoic acid, straight-chain or
 branched dodecanoic acid, straight-chain or branched
 tridecanoic acid, straight-chain or branched
 tetradecanoic acid, straight-chain or branched
 10 pentadecanoic acid, straight-chain or branched
 hexadecanoic acid, straight-chain or branched
 heptadecanoic acid, straight-chain or branched
 octadecanoic acid, straight-chain or branched
 hydroxyoctadecanoic acid, straight-chain or branched
 15 nonadecanoic acid, straight-chain or branched
 eicosanoic acid, straight-chain or branched
 heneicosanoic acid, straight-chain or branched
 docosanoic acid, straight-chain or branched tricosanoic
 and straight-chain or branched tetracosanoic acid, and
 20 unsaturated fatty acids such as acrylic acid, straight-
 chain or branched butenoic acid, straight-chain or
 branched pentenoic acid, straight-chain or branched
 hexenoic acid, straight-chain or branched heptenoic
 acid, straight-chain or branched octenoic acid,
 25 straight-chain or branched nonenoic acid, straight-
 chain or branched decenoic acid, straight-chain or

branched undecenoic acid, straight-chain or branched
dodecenoic acid, straight-chain or branched tridecenoic
acid, straight-chain or branched tetradecenoic acid,
straight-chain or branched pentadecenoic acid,
5 straight-chain or branched hexadecenoic acid, straight-
chain or branched heptadecenoic acid, straight-chain or
branched octadecenoic acid, straight-chain or branched
hydroxyoctadecenoic acid, straight-chain or branched
nonadecenoic acid, straight-chain or branched
10 eicosenoic acid, straight-chain or branched
heneicosenoic acid, straight-chain or branched
docosenoic acid, straight-chain or branched tricosenoic
acid and straight-chain or branched tetracosenoic acid,
as well as mixtures thereof.

15 [0151] As polybasic acids there may be mentioned
dibasic acids, trimellitic acid, and the like, but
dibasic acids are preferred from the standpoint of
refrigerant atmosphere/low temperature anti-separation
property. A dibasic acid may be either a linear
20 dibasic acid or a cyclic dibasic acid. In the case of
a linear dibasic acid, it may be either straight-chain
or branched, and either saturated or unsaturated.
Linear dibasic acids are preferably C2-16 linear
dibasic acids, and as specific examples there may be
25 mentioned ethanedioic acid, propanedioic acid,
straight-chain or branched butanedioic acid, straight-

chain or branched pentanedioic acid, straight-chain or
 branched hexanedioic acid, straight-chain or branched
 heptanedioic acid, straight-chain or branched
 octanedioic acid, straight-chain or branched
 5 nonanedioic acid, straight-chain or branched
 decanedioic acid, straight-chain or branched
 undecanedioic acid, straight-chain or branched
 dodecanedioic acid, straight-chain or branched
 tridecanedioic acid, straight-chain or branched
 10 tetradecanedioic acid, straight-chain or branched
 heptadecanedioic acid, straight-chain or branched
 hexadecanedioic acid, straight-chain or branched
 hexenedioic acid, straight-chain or branched
 heptenedioic acid, straight-chain or branched
 15 octenedioic acid, straight-chain or branched
 nonenedioic acid, straight-chain or branched
 decenedioic acid, straight-chain or branched
 undecenedioic acid, straight-chain or branched
 dodecenedioic acid, straight-chain or branched
 20 tridecenedioic acid, straight-chain or branched
 tetradecenedioic acid, straight-chain or branched
 heptadecenedioic acid, straight-chain or branched
 hexadecenedioic acid and mixtures thereof. As cyclic
 dibasic acids there may be mentioned 1,2-
 25 cyclohexanedicarboxylic acid, 4-cyclohexene-1,2-
 dicarboxylic acid and aromatic dicarboxylic acids.

Linear dibasic acids are preferred from the standpoint of stability.

5 [0152] The acid forming the ester oil agent of the invention may be either a monobasic acid or a polybasic acid as mentioned above, but is preferably a monobasic acid from the standpoint of achieving a more excellent enhancing effect on the abrasion resistance and friction properties.

10 [0153] Any combination of alcohols and acids may be employed for the ester oil agent, with no particular restrictions, and as examples there may be mentioned esters comprising the following combinations (i) to (vii).

15 [0154] (i) Esters of monohydric alcohols and monobasic acids

[0155] (ii) Esters of polyhydric alcohols and monobasic acids

[0156] (iii) Esters of monohydric alcohols and polybasic acids

20 [0157] (iv) Esters of polyhydric alcohols and polybasic acids

[0158] (v) Esters comprising mixtures of monohydric alcohols and polyhydric alcohols, and polybasic acids

[0159] (vi) Esters comprising polyhydric alcohols and mixtures of monobasic acids and polybasic acids

25 [0160] (vii) Esters comprising mixtures of

monohydric alcohols and polyhydric alcohols, and monobasic and polybasic acids.

[0161] Each of the esters of (ii) to (vii) above may be a complete ester wherein all of the hydroxyl groups of the polyhydric alcohol or all of the carboxyl groups of the polybasic acid are esterified, or a partial ester wherein some of the hydroxyl groups or carboxyl groups remain, but complete esters are preferred from the standpoint of reducing the effect on the refrigerant atmosphere/low temperature anti-separation property, while partial esters are preferred from the standpoint of enhancing effect on the abrasion resistance.

[0162] Among the esters of (i) to (vii) above there are preferred (i) esters of monohydric alcohols and monobasic acids and (iii) esters of monohydric alcohols and polybasic acids, with the esters of (i) being more preferred. These esters have a very significant effect on enhancement of abrasion resistance and friction properties, while also minimizing the effects on the refrigerant atmosphere/low temperature anti-separation property, and thermal-oxidative stability.

[0163] For the esters of (i), the number of carbon atoms of the monobasic acid is preferably 10 or greater, more preferably 12 or greater and more preferably 14 or greater, from the standpoint of enhancing the abrasion

resistance and friction property when used in combination with the phosphorus-based extreme pressure agent, and from the standpoint of thermal-oxidative stability. The number of carbon atoms of the monobasic acid is also preferably no greater than 28, more preferably no greater than 26 and more preferably no greater than 24 from the standpoint of the refrigerant atmosphere/low temperature anti-separation property. As such esters there may be mentioned methyl stearate, butyl stearate, methyl palmitate and isopropyl palmitate.

[0164] The monobasic acids and monohydric alcohols forming the esters of (i) above may each be straight-chain or branched, but esters of straight-chain monobasic acids are preferred from the standpoint of friction properties.

[0165] The dibasic acids in the esters of (iii) above are preferably linear. As such esters there may be mentioned diisodecyl adipate, diisononyl adipate and diisobutyl adipate.

[0166] The refrigerating machine oil composition of the invention will sometimes contain an ester as the base oil, and the ester used as the base oil is preferably at least one selected from among polyol esters and diesters of alicyclic dibasic acids, while the ester oil agent is preferably at least one selected

from among esters of monohydric alcohols and monobasic acids and esters of linear dibasic acids and monohydric alcohols.

[0167] As monohydric alcohol oil agents there may be mentioned the monohydric alcohols mentioned above for the ester oil agent. The total number of carbon atoms of the monohydric alcohol oil agent is preferably 6 or greater, more preferably 8 or greater and most preferably 10 or greater from the standpoint of enhancing the abrasion resistance and friction properties. On the other hand, since separation will tend to occur in the refrigerant atmosphere if the total number of carbon atoms is too high, it is preferably no greater than 20, more preferably no greater than 18 and most preferably no greater than 16.


[0168] Carboxylic acid oil agents may be monobasic acids or polybasic acids. As examples of such carboxylic acids there may be mentioned the monobasic acids and polybasic acids mentioned above for the ester oil agent. Monobasic acids are preferred from the standpoint of abrasion resistance and friction properties. The total number of carbon atoms in the carboxylic acid oil agent is preferably 6 or greater, more preferably 8 or greater and most preferably 10 or greater from the standpoint of enhancing the abrasion resistance and friction properties. On the other hand,

since separation will tend to occur in the refrigerant atmosphere if the total number of carbon atoms of the carboxylic acid oil agent is too high, it is preferably no greater than 20, more preferably no greater than 18 and most preferably no greater than 16.


[0169] As ether oil agents there may be mentioned etherified aliphatic 3-6 polyhydric alcohols, and etherified bimolecular condensates or trimolecular condensates of aliphatic 3-6 polyhydric alcohols.

[0170] Examples of etherified aliphatic 3-6 polyhydric alcohols include those represented by the following general formulas (28)-(33).


[Chemical Formula 17]




[Chemical Formula 18]




[Chemical Formula 19]




[Chemical Formula 20]



[Chemical Formula 21]



[Chemical Formula 22]



5 [wherein $\text{R}^{61}-\text{R}^{85}$ may be the same or different and each represents hydrogen or C1-18 straight-chain or branched alkyl, allyl, aralkyl, or a glycol ether residue represented by $-(\text{R}^a\text{O})_n-\text{R}^b$ (where R^a represents C2-6 alkylene, R^b represents C1-20 alkyl, allyl, aralkyl, and

10 n represents an integer of 1-10)].

[0171] As specific examples of aliphatic 3-6 polyhydric alcohols there may be mentioned glycerin, trimethylolpropane, erythritol, pentaerythritol,


15 arabitol, sorbitol and mannitol. As groups for $\text{R}^{61}-\text{R}^{85}$ in general formulas (28) to (33) above there may be mentioned methyl, ethyl, n-propyl, isopropyl, butyl isomers, pentyl isomers, hexyl isomers, heptyl isomers, octyl isomers, nonyl isomers, decyl isomers, undecyl

20 isomers, dodecyl isomers, tridecyl isomers, tetradecyl isomers, pentadecyl isomers, hexadecyl isomers,


heptadecyl isomers, octadecyl isomers, phenyl and benzyl. The aforementioned etherified forms also include partial etherified forms wherein some of R^{61} - R^{85} are hydrogen.

5 [0172] As etherified bimolecular condensates or trimolecular condensates of aliphatic 3-6 polyhydric alcohols there may be mentioned homogeneous or heterogeneous condensates among the compounds represented by general formulas (28)-(33). For example,
 10 etherified bimolecular condensates and trimolecular condensates of alcohols represented by general formula (28) are represented by general formulas (34) and (35), respectively. Etherified bimolecular condensates or trimolecular condensates of alcohols represented by
 15 general formula (30) are represented by general formulas (36) and (37), respectively.


[Chemical Formula 23]




[Chemical Formula 24]



[Chemical Formula 25]



[Chemical Formula 26]



[wherein $\text{R}^{61}-\text{R}^{63}$ and $\text{R}^{71}-\text{R}^{74}$ have the same definitions as $\text{R}^{61}-\text{R}^{63}$ in formula (28) and $\text{R}^{71}-\text{R}^{74}$ in formula (31), respectively].

[0173] As specific examples of etherified bimolecular condensates or trimolecular condensates of aliphatic 3-6 polyhydric alcohols there may be mentioned diglycerin, ditrimethylolpropane, dipentaerythritol, disorbitol, triglycerin, tritrimethylolpropane, tripentaerythritol and trisorbitol.

[0174] As specific examples of ether oil agents represented by general formulas (28) to (37) there may be mentioned glycerin trihexylether, glycerin dimethyloctyl triether, glycerin di(methyloxyisopropylene)dodecyl triether, glycerin diphenyloctyl triether, glycerin di(phenyloxyisopropylene)dodecyl triether,

trimethylolpropane trihexylether, trimethylolpropane
 dimethyloctyl triether, trimethylolpropane
 di(methyloxyisopropylene)dodecyl triether,
 pentaerythritol tetrahexylether, pentaerythritol
 5 trimethyloctyltetraether, pentaerythritol
 tri(methyloxyisopropylene)dodecyltetraether, sorbitol
 hexapropylether, sorbitol tetramethyloctylpentaether,
 sorbitol hexa(methyloxyisopropylene)ether, diglycerin
 tetrabutylether, diglycerin dimethyldioctyltetraether,
 10 diglycerin tri(methyloxyisopropylene)dodecyltetraether,
 triglycerin pentaethylether, triglycerin
 trimethyldioctylpentaether, triglycerin
 tetra(methyloxyisopropylene)decylpentaether,
 ditrimethylolpropane tetrabutylether,
 15 ditrimethylolpropane dimethyldioctyltetraether,
 ditrimethylolpropane
 tri(methyloxyisopropylene)dodecyltetraether,
 tritrimethylolpropane pentaethylether,
 tritrimethylolpropane trimethyldioctylpentaether,
 20 tritrimethylolpropane
 tetra(methyloxyisopropylene)decylpentaether,
 dipentaerythritol hexapropylether, dipentaerythritol
 pentamethyloctyl hexaether, dipentaerythritol
 hexa(methyloxyisopropylene)ether, tripentaerythritol
 25 octapropylether, tripentaerythritol pentamethyloctyl
 hexaether, tripentaerythritol

hexa(methyloxyisopropylene)ether, disorbitol
octamethyldioctyl decaether and disorbitol
deca(methyloxyisopropylene)ether. Preferred among
these are glycerin diphenyloctyl triether,
5 trimethylolpropane di(methyloxyisopropylene)dodecyl
triether, pentaerythritol tetrahexylether, sorbitol
hexapropylether, diglycerin dimethyldioctyltetraether,
triglycerin tetra(methyloxyisopropylene)decylpentaether,
dipentaerythritol hexapropylether and
10 tripentaerythritol pentamethyloctyl hexaether.

[0175] Any single ester oil agent, monohydric
alcohol oil agent, carboxylic acid oil agent or ether
oil agent may be used alone, or two or more may be used
in combination, together with the phosphorus-based
15 extreme pressure agent in the refrigerating machine oil
composition of the invention. Preferred among these
oil agents are those comprising ester oil agents as
essential components, from the standpoint of achieving
a satisfactory balance with high levels of abrasion
20 resistance, friction properties, anti-separation
property and stability. Ester oil agents not only
provide a high level of abrasion resistance and
friction properties, but also result in a more
excellent anti-separation property compared to
25 monohydric alcohol oil agents or ether oil agents, and
superior stability than carboxylic acid oil agents.

[0176] Although the content of the oil agent may be as desired, it is preferably 0.01 wt% or greater, more preferably 0.05 wt% or greater and more preferably 0.1 wt% or greater based on the total amount of the composition, from the standpoint of an excellent enhancing effect on the abrasion resistance and friction properties by use with the phosphorus-based extreme pressure agent. The content is also preferably no greater than 10 wt%, more preferably no greater than 7.5 wt% and even more preferably no greater than 5 wt% based on the total amount of the composition, from the standpoint of a more excellent refrigerant atmosphere/low temperature anti-separation property, and thermal-oxidative stability of the refrigerating machine oil composition.

[0177] The proportion of the phosphorus-based extreme pressure agent and the oil agent is preferably 1:10-10:1, more preferably 1:5-5:1, and even more preferably 1:3-1:1, based on weight. If the proportion of the phosphorus-based extreme pressure agent and the oil agent is within this range, it will be possible to achieve further enhancement in abrasion resistance and friction properties.

[0178] As mentioned above, the refrigerating machine oil composition of the invention comprises a prescribed base oil, phosphorus-based extreme pressure agent and


oil agent as essential components, but it may also further contain benzotriazole and/or its derivatives, epoxy compounds, or other additives, as explained below.

[0179] (Benzotriazole and/or its derivatives)

5 [0180] The refrigerating machine oil composition of the invention also preferably contains benzotriazole and/or a derivative thereof. Adding benzotriazole and/or a derivative thereof will further increase the enhancing effect on the abrasion resistance and
10 friction properties.

[0181] Benzotriazole is the compound represented by the following formula (38).


[Chemical Formula 27]




(38)

15 [0182] As examples of benzotriazole derivatives there may be mentioned alkylbenzotriazoles represented by the following general formula (39), and (alkyl)aminoalkylbenzotriazoles represented by general formula (40).

20 [Chemical Formula 28]



[Chemical Formula 29]



[0183] In formula (39), R^{86} represents a C1-4
 5 straight-chain or branched alkyl group, and preferably
 methyl or ethyl, and x represents an integer of 1-3,
 and preferably 1 or 2. As examples of R^{86} there may be
 mentioned methyl, ethyl, n-propyl, isopropyl, n-butyl,
 isobutyl, sec-butyl and tert-butyl. As
 10 alkylbenzotriazoles represented by formula (39) there
 are preferred compounds wherein R^{86} is methyl or ethyl
 and x is 1 or 2, particularly from the standpoint of
 achieving excellent oxidation resistance, and as
 examples there may be mentioned
 15 methylbenzotriazole(tolyltriazole),
 dimethylbenzotriazole, ethylbenzotriazole,
 ethylmethylbenzotriazole, diethylbenzotriazole, or
 mixtures thereof.

[0184] In formula (40), R^{87} represents a C1-4

straight-chain or branched alkyl group, and preferably methyl or ethyl, R^{88} represents methylene or ethylene, R^{89} and R^{90} may be the same or different and each represents hydrogen or a C1-18 straight-chain or branched alkyl group, and preferably a C1-12 straight-chain or branched alkyl group, and y represents an integer of 0-3, and preferably 0 or 1. As examples of R^{87} there may be mentioned methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl and tert-butyl. As examples of R^{89} and R^{90} , independently, there may be mentioned hydrogen, and alkyl groups such as methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, sec-butyl, tert-butyl, straight-chain or branched pentyl, straight-chain or branched hexyl, straight-chain or branched heptyl, straight-chain or branched octyl, straight-chain or branched nonyl, straight-chain or branched decyl, straight-chain or branched undecyl, straight-chain or branched dodecyl, straight-chain or branched tridecyl, straight-chain or branched tetradecyl, straight-chain or branched pentadecyl, straight-chain or branched hexadecyl, straight-chain or branched heptadecyl and straight-chain or branched octadecyl.

[0185] As (alkyl)aminobenzotriazoles represented by formula (40) above there are preferably used dialkylaminoalkylbenzotriazole and

dialkylaminoalkyltolyltriazole, wherein R^{87} is methyl,
 y is 0 or 1, R^{88} is methylene or ethylene and R^{89} and
 R^{90} are C1-12 straight-chain or branched alkyl groups,
 or mixtures thereof, from the standpoint of achieving
 particularly excellent oxidation resistance. As
 5 examples of these dialkylaminoalkylbenzotriazoles
 there may be mentioned
 dimethylaminomethylbenzotriazole,
 diethylaminomethylbenzotriazole, di-(straight-chain or
 10 branched)-propylaminomethylbenzotriazole, di-
 (straight-chain or branched)-
 butylaminomethylbenzotriazole, di-(straight-chain or
 branched)-pentylaminomethylbenzotriazole, di-
 (straight-chain or branched)-
 15 hexylaminomethylbenzotriazole, di-(straight-chain or
 branched)-heptylaminomethylbenzotriazole, di-
 (straight-chain or branched)-
 octylaminomethylbenzotriazole, di-(straight-chain or
 branched)-nonylaminomethylbenzotriazole, di-(straight-
 20 chain or branched)-decylaminomethylbenzotriazole, di-
 (straight-chain or branched)-
 undecylaminomethylbenzotriazole and di-(straight-chain
 or branched)-dodecylaminomethylbenzotriazole;
 dimethylaminoethylbenzotriazole,
 25 diethylaminoethylbenzotriazole, di-(straight-chain or
 branched)propylaminoethylbenzotriazole, di-(straight-

chain or branched)butylaminoethylbenzotriazole, di-
 (straight-chain or
 branched)pentylaminoethylbenzotriazole, di-(straight-
 chain or branched)hexylaminoethylbenzotriazole, di-
 5 (straight-chain or
 branched)heptylaminoethylbenzotriazole, di-(straight-
 chain or branched)octylaminoethylbenzotriazole, di-
 (straight-chain or
 branched)nonylaminoethylbenzotriazole, di-(straight-
 10 chain or branched)decylaminoethylbenzotriazole, di-
 (straight-chain or
 branched)undecylaminoethylbenzotriazole and di-
 (straight-chain or branched)-
 dodecylaminoethylbenzotriazole;
 15 dimethylaminomethyltolyltriazole,
 diethylaminomethyltolyltriazole, di-(straight-chain or
 branched)-propylaminomethyltolyltriazole, di-
 (straight-chain or branched)-
 butylaminomethyltolyltriazole, di-(straight-chain or
 branched)-pentylaminomethyltolyltriazole, di-
 20 (straight-chain or branched)-
 hexylaminomethyltolyltriazole, di-(straight-chain or
 branched)-heptylaminoethyltolyltriazole, di-
 (straight-chain or branched)-
 25 octylaminomethyltolyltriazole, di-(straight-chain or
 branched)-nonylaminoethyltolyltriazole, di-(straight-

chain or branched)-decylaminomethyltolyltriazole, di-
(straight-chain or branched)-
undecylaminomethyltolyltriazole and di-(straight-chain
or branched)-dodecylaminomethyltolyltriazole;
5 dimethylaminoethyltolyltriazole,
diethylaminoethyltolyltriazole, di-(straight-chain or
branched)propylaminoethyltolyltriazole, di-(straight-
chain or branched)butylaminoethyltolyltriazole, di-
(straight-chain or
10 branched)pentylaminoethyltolyltriazole, di-(straight-
chain or branched)hexylaminoethyltolyltriazole, di-
(straight-chain or
branched)heptylaminoethyltolyltriazole, di-(straight-
chain or branched)octylaminoethyltolyltriazole, di-
15 (straight-chain or
branched)nonylaminoethyltolyltriazole, di-(straight-
chain or branched)decylaminoethyltolyltriazole, di-
(straight-chain or
branched)undecylaminoethyltolyltriazole and di-
20 (straight-chain or branched)-
dodecylaminoethyltolyltriazole; or mixtures thereof.

[0186] Although the content of the benzotriazole
and/or its derivative in the refrigerating machine oil
composition of the invention may be as desired, it is
25 preferably 0.001 wt% or greater and more preferably
0.005 wt% or greater based on the total weight of the

composition. If it is less than 0.001 wt%, the enhancing effect of the benzotriazole and/or its derivative on the abrasion resistance and friction properties may be insufficient. The content of the benzotriazole and/or its derivative is preferably no greater than 1.0 wt% and more preferably no greater than 0.5 wt% based on the total weight of the composition. If the content is greater than 1.0 wt%, a commensurate enhancing effect on the abrasion resistance and friction properties will not be obtained, thus presenting a disadvantage in terms of economy.

[0187] (Epoxy compound)

[0188] For further improved friction properties and thermal/hydrolytic stability, the refrigerating machine oil composition of the invention preferably contains at least one epoxy compound selected from the group consisting of:


- (1) phenylglycidyl ether-type epoxy compounds
- (2) alkylglycidyl ether-type epoxy compounds
- (3) glycidyl ester-type epoxy compounds
- (4) allyloxirane compounds
- (5) alkyloxirane compounds
- (6) alicyclic epoxy compounds
- (7) epoxidated fatty acid monoesters, and
- (8) epoxidated vegetable oils.

[0189] (1) Specific examples of phenylglycidyl ether-type epoxy compounds include phenylglycidyl ethers and alkylphenylglycidyl ethers. As alkylphenylglycidyl ethers there may be mentioned those having one to three C1-13 alkyl groups, among which those having one C4-10 alkyl group such as, for example, *n*-butylphenylglycidyl ether, *i*-butylphenylglycidyl ether, *sec*-butylphenylglycidyl ether, *tert*-butylphenylglycidyl ether, pentylphenylglycidyl ether, hexylphenylglycidyl ether, heptylphenylglycidyl ether, octylphenylglycidyl ether, nonylphenylglycidyl ether and decylphenylglycidyl ether, are preferred.

[0190] (2) Specific examples of alkylglycidyl ether-type epoxy compounds include decylglycidyl ether, undecylglycidyl ether, dodecylglycidyl ether, tridecylglycidyl ether, tetradecylglycidyl ether, 2-ethylhexylglycidyl ether, neopentyl glycol diglycidyl ether, trimethylolpropane triglycidyl ether, pentaerythritoltetraglycidyl ether, 1,6-hexanediol diglycidyl ether, sorbitol polyglycidyl ether, polyalkylene glycol monoglycidyl ethers and polyalkylene glycol diglycidyl ethers.

[0191] (3) As specific examples of glycidyl ester-type epoxy compounds there may be mentioned compounds represented by the following general formula (41):

[Chemical Formula 30]



(wherein R represents a C1-18 hydrocarbon group).

[0192] In formula (41), R represents a C1-18 hydrocarbon group, and as such hydrocarbon groups there may be mentioned C1-18 alkyl, C2-18 alkenyl, C5-7 cycloalkyl, C6-18 alkylcycloalkyl, C6-10 aryl, C7-18 alkylaryl and C7-18 arylalkyl. Preferred among these are alkylphenyl groups such as C5-15 alkyl, C2-15 alkenyl, phenyl and C1-4 alkyl.

[0193] Specific examples of preferred glycidyl ester-type epoxy compounds include glycidyl-2,2-dimethyl octanoate, glycidyl benzoate, glycidyl-tert-butyl benzoate, glycidyl acrylate and glycidyl methacrylate.


[0194] (4) Specific examples of allyloxirane compounds include 1,2-epoxystyrene and alkyl-1,2-epoxystyrene.

[0195] (5) Specific examples of alkyloxirane compounds include 1,2-epoxybutane, 1,2-epoxypentane, 1,2-epoxyhexane, 1,2-epoxyheptane, 1,2-epoxyoctane, 1,2-epoxynonane, 1,2-epoxydecane, 1,2-epoxyundecane, 1,2-epoxydodecane, 1,2-epoxytridecane, 1,2-epoxytetradecane, 1,2-epoxypentadecane, 1,2-epoxyhexadecane, 1,2-epoxyheptadecane, 1,1,2-epoxyoctadecane, 2-epoxynonadecane and 1,2-

epoxyeicosane.

[0196] (6) As alicyclic epoxy compounds there may be mentioned compounds wherein the carbon atoms forming the epoxy group directly form an alicyclic ring, such as compounds represented by the following general formula (42):

[Chemical Formula 31]



[0197] Specific examples of alicyclic epoxy compounds include 1,2-epoxycyclohexane, 1,2-epoxycyclopentane, 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexanecarboxylate, bis(3,4-epoxycyclohexylmethyl) adipate, exo-2,3-epoxynorbornane, bis(3,4-epoxy-6-methylcyclohexylmethyl) adipate, 2-(7-oxabicyclo[4.1.0]hept-3-yl)-spiro(1,3-dioxane-5,3'-[7]oxabicyclo[4.1.0]heptane, 4-(1'-methylepoxyethyl)-1,2-epoxy-2-methylcyclohexane and 4-epoxyethyl-1,2-epoxycyclohexane.

[0198] (7) Specific examples of epoxidated fatty acid monoesters include esters of epoxidated C12-20 fatty acids and C1-8 alcohols, phenols or alkylphenols. Particularly preferred for use are butyl, hexyl, benzyl, cyclohexyl, methoxyethyl, octyl, phenyl and butylphenyl esters of epoxystearic acid.

[0199] (8) Specific examples of epoxidated vegetable oils include epoxy compounds derived from vegetable oils such as soybean oil, linseed oil, cotton oil, and the like.

5 [0200] Among these epoxy compounds, there are preferred phenylglycidyl ether-type epoxy compounds, glycidyl ester-type epoxy compounds, alicyclic epoxy compounds and epoxidated fatty acid monoesters, with glycidyl ester-type epoxy compounds and alicyclic epoxy
10 compounds being more preferred, as they will allow further enhanced thermal/hydrolytic stability.

[0201] When these epoxy compounds are included in the refrigerating machine oil composition of the invention, their contents are not particularly
15 restricted, but the epoxy compounds will usually be added to contents of 0.1-5.0 wt% and more preferably 0.2-2.0 wt% based on the total weight of the refrigerating machine oil composition (total weight of the base oil and all additives).

20 [0202] Needless to mention, two or more of the aforementioned epoxy compounds may be used in combination.

[0203] (Other additives)

[0204] For even further increased performance, the
25 refrigerating machine oil composition of the invention may, if necessary, contain conventional publicly known

refrigerating machine oil additives including, for example, phenol-based antioxidants such as di-tert-butyl-p-cresol and bisphenol A, amine-based antioxidants such as phenyl- α -naphthylamine and N,N-di(2-naphthyl)-p-phenylenediamine, anti-abrasion agents such as zinc dithiophosphate, phosphorus-based extreme pressure agents such as chlorinated paraffin and sulfur-based extreme pressure agents, antifoaming agents such as silicone-based agents, viscosity index improvers, pour point depressants, detergent dispersants and the like, either alone or as combinations of different types. There are no particular restrictions on the total amount of addition of such additives, but it is preferably no greater than 10 wt% and more preferably no greater than 5 wt% based on the total weight of the refrigerating machine oil composition (the total weight of the base oil and all additives).

[0205] There are no particular restrictions on the volume resistivity of the refrigerating machine oil composition of the invention, but it is preferably $1.0 \times 10^9 \Omega \cdot \text{cm}$. High electrical insulation will tend to be required especially for use in a closed-type refrigerating machine. Here, the volume resistivity refers to the value [$\Omega \cdot \text{cm}$] measured at 25°C according to JIS C 2101: "Electrical Insulating Oil Test Method".

[0206] There are no particular restrictions on the moisture content of the refrigerating machine oil composition of the invention, but it is preferably no greater than 200 ppm, more preferably no greater than 100 ppm and most preferably no greater than 50 ppm, based on the total of the refrigerating machine oil composition. Particularly when the composition is to be used in a closed-type refrigerating machine, a smaller moisture content is desired from the viewpoint of its effect on the thermal/hydrolytic stability and electrical insulation property of the oil.

[0207] The acid value of the refrigerating machine oil composition of the invention is not particularly restricted, but in order to prevent corrosion of the metal used in the refrigerating machine or pipes, it is preferably no greater than 0.1 mgKOH/g and more preferably no greater than 0.05 mgKOH/g. Here, the acid value refers to the value [mgKOH/g] measured according to JIS K 2501: "Petroleum Products and Lubricating Oils - Neutralization Value Test Method".

[0208] The ash content of the refrigerating machine oil composition of the invention is also not particularly restricted, but in order to increase the thermal/hydrolytic stability of the refrigerating machine oil composition of the invention and inhibit production of sludge, it is preferably no greater than

100 ppm and more preferably no greater than 50 ppm.
According to the invention, the ash content refers to
the value [ppm] measured according to JIS K 2272:
"Crude Oil and Petroleum Product Ash Content and
5 Sulfated Ash Test Method".

[0209] The refrigerant used in a refrigerating
machine employing the refrigerating machine oil
composition of the invention is an HFC refrigerant, a
fluoroether-based refrigerant such as perfluoroether, a
10 non-fluoroether-based refrigerant such as dimethyl
ether or a natural refrigerant such as carbon dioxide
ammonia or a hydrocarbon, and any of these may be used
alone or in mixtures of two or more different types.

[0210] As HFC refrigerants there may be mentioned
15 C1-3 and preferably C1-2 hydrofluorocarbons. As
specific examples there may be mentioned HFCs such as
difluoromethane (HFC-32), trifluoromethane (HFC-23),
pentafluoroethane (HFC-125), 1,1,2,2-tetrafluoroethane
(HFC-134), 1,1,1,2-tetrafluoroethane (HFC-134a), 1,1,1-
20 trifluoroethane (HFC-143a), 1,1-difluoroethane (HFC-
152a) and the like, or mixtures of two or more thereof.
These refrigerants may be appropriately selected
depending on the purpose of use and the required
performance, but as preferred examples there may be
25 mentioned HFC-32 alone; HFC-23 alone; HFC-134a alone;
HFC-125 alone; mixture of HFC-134a/HFC-32 = 60-80

wt%/40-20 wt%; mixture of HFC-32/HFC-125 = 40-70
 wt%/60-30 wt%; mixture of HFC-125/HFC-143a = 40-60
 wt%/60-40 wt%; mixture of HFC-134a/HFC-32/HFC-125 = 60
 wt%/30 wt%/10 wt%; mixture of HFC-134a/HFC-32/HFC-125 =
 5 40-70 wt%/15-35 wt%/5-40 wt%; and mixture of HFC-
 125/HFC-134a/HFC-143a = 35-55 wt%/1-15 wt%/40-60 wt%.

More specifically, there may be mentioned mixture of
 HFC-134a/HFC-32 = 70/30 wt%; mixture of HFC-32/HFC-125
 = 60/40 wt%; mixture of HFC-32/HFC-125 = 50/50 wt%

10 (R410A); mixture of HFC-32/HFC-125 = 45/55 wt% (R410B);
 mixture of HFC-125/HFC-143a = 50/50 wt% (R507C);
 mixture of HFC-32/HFC-125/HFC-134a = 30/10/60 wt%;
 mixture of HFC-32/HFC-125/HFC-134a = 23/25/52 wt%
 (R407C); mixture of HFC-32/HFC-125/HFC-134a = 25/15/60
 15 wt% (R407E); and mixture of HFC-125/HFC-134a/HFC-143a =
 44/4/52 wt% (R404A).

[0211] As natural refrigerants there may be
 mentioned carbon dioxide, ammonia, and hydrocarbons.
 Preferred hydrocarbon refrigerants are those which are
 20 gases at 25°C, 1 atmosphere. Specifically, these
 include C1-5 and preferably C1-4 alkanes, cycloalkanes,
 alkenes and mixtures thereof. As specific examples
 there may be mentioned methane, ethylene, ethane,
 propylene, propane, cyclopropane, butane, isobutane,
 25 cyclobutane, methylcyclopropane or mixtures of two or
 more thereof. Among these, propane, butane, isobutane,

and their mixtures are preferred.

[0212] The refrigerating machine oil composition of the invention will ordinarily be in the form of a refrigerating machine fluid composition in admixture with the aforementioned refrigerant in a refrigerating machine. There are no particular restrictions on the mixing ratio of the refrigerating machine oil and refrigerant in the fluid composition, but it is preferably 1-500 parts by weight and more preferably 2-400 parts by weight of the refrigerating machine oil with respect to 100 parts by weight of the refrigerant.

[0213] The refrigerating machine oil composition of the invention provides a satisfactory balance between all of the required performance properties including lubricity, refrigerant miscibility, low temperature flow property and stability, and it may be suitably used in a refrigeration device or heat pump comprising a reciprocating or rotating open-type or semi-closed-type or closed-type compressor. Particularly when used in a refrigeration device employing aluminum-based members, it allows both the anti-abrasion property and thermal/chemical stability of the aluminum-based members to be kept at a high level. More specifically, such refrigeration devices include automobile air conditioners, dehumidifiers, refrigerators, refrigerated storage rooms, vending machines, showcases,

refrigerating apparatuses in chemical plants and the like, home air conditioners, package air conditioners, and water heater heat pumps. The refrigerating machine oil composition of the invention may be used in a reciprocating, rotating or centrifugal type of compressor.

[0214] A typical construction for a refrigerant circulation system which may employ the refrigerating machine oil composition of the invention comprises a refrigerant compressor, condenser, expansion mechanism and evaporator connected in that order along the flow path, and if necessary is also equipped with a drier in the flow path.

[0215] Refrigerant compressors may be exemplified by a high-pressure vessel compressor housing a motor comprising a rotor and a stator in a closed vessel holding refrigerating machine oil, a rotary shaft fitted on the rotor and a compressor section connected to the motor via the rotary shaft, wherein high-pressure refrigerant gas discharged from the compressor section accumulates in the closed vessel, or a low-pressure vessel compressor housing a motor comprising a rotor and a stator in a closed vessel holding refrigerating machine oil, a rotary shaft fitted on the rotor and a compressor section connected to the motor via the rotary shaft, wherein high-pressure refrigerant

gas discharged from the compressor section is directly expelled out of the closed vessel.

[0216] The insulating film used as an electrical insulating system material in the motor is preferably a crystalline plastic film having a glass transition temperature of 50°C or higher, and specifically, for example, at least one type of insulating film selected from the group consisting of polyethylene terephthalate, polybutylene terephthalate, polyphenylene sulfide, polyetherether ketone, polyethylene naphthalate, polyamideimide and polyimide, or a composite film comprising a resin layer having a high glass transition temperature coated on a film having a low glass transition temperature, from the standpoint of avoiding deterioration in tensile strength and electrical insulating property. The magnet wire used in the motor preferably has an enamel coating having a glass transition temperature of 120°C or higher, such as, for example, an enamel coating comprising a single layer of a polyester, polyesterimide, polyamide or polyamideimide, or comprising a composite coating of a layer with a low glass transition temperature as the lower layer and a layer with a high glass transition temperature as the upper layer. As composite coated enamel wires there may be mentioned those having a polyesterimide as the lower layer and a polyamideimide

as the upper layer (AI/EI), and those having a polyester as the lower layer and a polyamideimide as the upper layer (AI/PE).

[0217] The drying agent filling the drier is preferably synthetic zeolite composed of compound alkali metal salts of silicic acid and aluminic acid, having a pore size of no greater than 3.3 angstroms and a carbon dioxide gas absorption capacity of no greater than 1.0% at 25°C and a carbon dioxide partial pressure of 250 mmHg. As specific examples there may be mentioned XH-9, XH-10, XH-11 and XH-600 (trade names) by Union Showa Co., Ltd.

[Examples]

[0218] The present invention will now be explained in greater detail based on examples and comparative examples, with the understanding that these examples are in no way limitative on the invention.

[0219] [Examples 1-125, Comparative Examples 1-52]

For Examples 1-125 and Comparative Examples 1-52, the following base oils and additives were used to prepare refrigerating machine oil compositions having the compositions shown in Tables 1 to 20.

[0220] (Base oil)

Base oil 1: Tetraester of pentaerythritol and an equimolar mixture of 2-ethylhexanoic acid and 3,5,5-trimethylhexanoic acid (kinematic viscosity at 40°C:

68.5 mm²/s, pour point: -25°C)

Base oil 2: Diester of 1,2-cyclohexanedicarboxylic acid and 2-ethylhexanol (kinematic viscosity at 40°C: 15 mm²/s, pour point: -40°C)

5 Base oil 3: Random copolymer of vinyl ethyl ether and vinyl isobutyl ether (vinyl ethyl ether/vinyl isobutyl ether molar ratio: 7/1, number average molecular weight: 900, kinematic viscosity at 40°C: 68.5 mm²/s, kinematic viscosity at 100°C: 8 mm²/s, pour point: -40°C)

10 Base oil 4: Naphthene-based mineral oil (kinematic viscosity at 40°C: 56.6 mm²/s, pour point: -30°C)

Base oil 5: Polypropyleneglycol monomethylether (number average molecular weight: 1000, kinematic viscosity at 40°C: 46 mm²/s, kinematic viscosity at 15 100°C: 10 mm²/s, pour point: -40°C).

[0221] (Phosphorus-based extreme pressure agent)

A1: Tricresyl phosphate

A2: Triphenyl phosphate

20 A3: Tri(n-octyl) phosphate.

[0222] (Oil agent)

B1: Butyl stearate

B2: Diisobutyl adipate

B3: Diisodecyl adipate

25 B4: Glycerin monooleate

B5: Glycerin trioleate

B6: Oleyl alcohol

B7: Glyceryl ether

B8: Stearic acid.

[0223] (Other additives)

5 C1: Di-t-butyl-p-cresol

C2: Glycidyl-2,2'-dimethyl octanoate

C3: Benzotriazole.

[0224] Next, each of the refrigerating machine oil compositions of Examples 1-125 and Comparative Examples 10 1-52 were subjected to the evaluation tests described below. The row "Refrigerant" in Tables 1-21 shows the type of refrigerant used in the friction property and abrasion property evaluation test and the stability evaluation test.

15 [0225] [Friction property and abrasion property evaluation test 1]

The slide member of a FALEX Tester (ASTM D2714) was set in a pressure-resistant vessel, the refrigerant was introduced into the vessel, and a FALEX test was 20 carried out under the following conditions.

Test materials: Steel ring, steel block

Test initial temperature: 80°C

Test time: 1 hr

Sliding speed: 0.5 m/s

25 Load: 1250 N

Refrigerant atmosphere pressure: 500 kPa.

[0226] The frictional coefficient and oil temperature were measured every other second after the start of the FALEX test, and the mean values were calculated (hereinafter referred to as "mean frictional coefficient 1" and "mean oil temperature 1"). The block abrasion loss after completion of the test was determined in terms of volume reduction (hereinafter referred to as "abrasion volume 1"). The results are shown in Tables 1-20.

[0227] [Anti-separation property evaluation test 1]

Each refrigerating machine oil composition was cooled to a temperature of 5°C higher than the pour point of the base oil in the composition, and the outer appearance of the composition was visually examined. The results are shown in Tables 1-20. Letters A-D in the tables stand for the following conditions.

A: Transparent

B: Slight cloudiness

C: Opaque

D: Total separation of additives

[0228] [Stability evaluation test 1]

A shielded glass tube test was carried out according to JIS K 2211 using iron, copper and aluminum as catalysts, and the presence of sludge was observed after a period of 2 weeks at 200°C. The results are shown in Tables 1-20. Letter A in the tables indicates

that no sludge was found, and B indicates that sludge was found.

[0229] [Anti-separation property evaluation test 2]

First, base oils 1-5 were used to prepare test solutions comprising 20 vol% of each base oil and 80 vol% of refrigerant, and the bilayer separation temperature of the base oil and refrigerant was measured. The obtained results were as follows.

Base oil 1 and R410A: 10°C

Base oil 2 and R134a: -35°C

Base oil 3 and R410A: -50°C

Base oil 4 and R22: -8°C

Base oil 5 and R134a: -45°C.

[0230] An anti-separation property evaluation test was then conducted according to JIS K 2211. Specifically, a test solution was prepared comprising 20 vol% of the refrigerating machine oil composition and 80 vol% of refrigerant, the test solution was cooled to a temperature of 5°C higher than the bilayer separation temperature of the base oil in the composition, the outer appearance of the composition was visually observed, and the anti-separation property was evaluated based on the following scale. The results are shown in Tables 1-20.

A: Transparent

B: Slight cloudiness

C: Completely opaque

D: Separation of additives

[0231] [Stability evaluation test 2]

5 A shielded glass tube test was carried out according to JIS K 2211 using iron, copper and aluminum as catalysts, and the presence of sludge was observed after a period of 2 weeks at 175°C. The results are shown in Tables 1-20. Letter A in the tables indicates that no sludge was found, B indicates that a very small amount of sludge was found, and C indicates that a large amount of sludge was found.

10

[Table 1]

		Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Example 8	Example 9
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	0.5	-	-	0.5	-	-	0.5	-	-
	A2	-	0.5	-	-	0.5	-	-	0.5	-
	A3	-	-	0.5	-	-	0.5	-	-	0.5
	B1	0.5	0.5	0.5	-	-	-	-	-	-
	B2	-	-	-	0.5	0.5	0.5	-	-	-
	B3	-	-	-	-	-	-	0.5	0.5	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.10	0.12	0.13	0.11	0.13	0.13	0.13	0.14	0.14
Mean oil temp. 1 (°C)		84	85	86	84	85	87	85	86	88
Abrasion volume 1 (mm ³)		2.0	1.9	2.1	2.2	2.0	2.3	2.3	2.2	2.3
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 2]

		Example 10	Example 11	Example 12	Example 13	Example 14	Example 15	Example 16	Example 17	Example 18
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	0.1	1.0	2.0	-	-	-	-	-	-
	A2	-	-	-	0.1	1.0	2.0	-	-	-
	A3	-	-	-	-	-	-	0.1	1.0	2.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.14	0.12	0.14	0.14	0.14	0.14	0.14	0.14	0.14
Mean oil temp. 1 (°C)		92	88	91	92	89	92	89	90	93
Abrasion volume 1 (mm ³)		2.8	1.9	2.2	2.8	2.0	2.2	2.8	2.2	2.3
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 3]

		Example 19	Example 20	Example 21	Example 22	Example 23	Example 24	Example 25	Example 26	Example 27
Base oil		Base oil 1	Base oil 1	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.5	0.5	0.5	-	-	0.5	-	-	0.5
	A2	-	-	-	0.5	-	-	0.5	-	-
	A3	-	-	-	-	0.5	-	-	0.5	-
	B1	-	-	0.5	0.5	0.5	-	-	-	-
	B2	-	-	-	-	-	0.5	0.5	0.5	-
	B3	-	-	-	-	-	-	-	-	0.5
	B4	0.5	-	-	-	-	-	-	-	-
	B5	-	0.5	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.13	0.15	0.12	0.13	0.13	0.12	0.13	0.14	0.12
Mean oil temp. 1 (°C)		94	94	88	89	91	90	92	92	91
Abrasion volume 1 (mm ³)		2.7	2.8	2.6	2.8	2.9	2.7	2.9	2.9	2.8
Anti-separation property 1		B	B	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 4]

		Example 28	Example 29	Example 30	Example 31	Example 32	Example 33	Example 34	Example 35	Example 36
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	-	-	0.1	1.0	2.0	-	-	-	-
	A2	0.5	-	-	-	-	0.1	1.0	2.0	-
	A3	-	0.5	-	-	-	-	-	-	0.1
	B1	-	-	0.1	1.0	2.0	-	-	-	-
	B2	-	-	-	-	-	0.1	1.0	2.0	-
	B3	0.5	0.5	-	-	-	-	-	-	1.0
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.13	0.14	0.14	0.12	0.13	0.14	0.12	0.13	0.14
Mean oil temp. 1 (°C)		92	93	94	90	93	94	91	94	94
Abrasion volume 1 (mm ³)		2.8	2.9	3.1	2.5	2.8	3.1	2.6	2.9	3.1
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 5]

		Example 37	Example 38	Example 39	Example 40	Example 41	Example 42	Example 43	Example 44
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 1	Base oil 1	Base oil 3	Base oil 3
Additive (wt%)	A1	-	-	0.5	0.5	0.5	-	0.5	-
	A2	-	-	-	-	-	0.5	-	0.5
	A3	1.0	2.0	-	-	-	-	-	-
	B1	-	-	-	-	0.5	-	0.5	-
	B2	-	-	-	-	-	0.5	-	-
	B3	1.0	2.0	-	-	-	-	-	0.5
	B4	-	-	0.5	-	-	-	-	-
	B5	-	-	-	0.5	-	-	-	-
	C1	-	-	-	-	0.1	0.1	0.1	0.1
	C2	-	-	-	-	0.5	0.5	0.5	0.5
	C3	-	-	-	-	-	0.001	-	0.001
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.12	0.13	0.12	0.14	0.10	0.08	0.11	0.10
Mean oil temp. 1 (°C)		91	94	94	94	83	82	87	85
Abrasion volume 1 (mm ³)		2.8	3.0	3.1	3.1	1.9	1.5	2.5	2.2
Anti-separation property 1		A	A	B	B	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A

[Table 6]

		Example 45	Example 46	Example 47	Example 48	Example 49	Example 50
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	1.0	1.0	1.0	1.0	1.0	1.0
	A2	-	-	-	-	-	-
	A3	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	-	-	1.0	-	-	1.0
	B5	-	1.0	-	-	1.0	-
	C1	1.0	-	-	1.0	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.14	0.15	0.16	0.15	0.15	0.16
Mean oil temp. 1 (°C)		95	94	100	94	97	95
Abrasion volume 1 (mm ³)		2.9	3.1	2.8	3.1	2.8	3.0
Anti-separation property 1		B	C	D	B	C	D
Stability 1		B	A	A	B	A	A
Anti-separation property 2		A	B	B	A	B	B
Stability 2		A	A	A	A	A	A

[Table 7]

		Comp. Ex. 1	Comp. Ex. 2	Comp. Ex. 3	Comp. Ex. 4	Comp. Ex. 5	Comp. Ex. 6	Comp. Ex. 7	Comp. Ex. 8
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	-	1.0	-	-	-	-	-	-
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	-	-	1.0	-	-	-	-	-
	B2	-	-	-	1.0	-	-	-	-
	B3	-	-	-	-	1.0	-	-	-
	B6	-	-	-	-	-	1.0	-	-
	B7	-	-	-	-	-	-	1.0	-
	B8	-	-	-	-	-	-	-	1.0
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.17	0.19	0.17	0.18	0.19	0.16	0.15	0.13
Mean oil temp. 1 (°C)		95	99	94	98	99	94	95	93
Abrasion volume 1 (mm ³)		2.9	2.9	3.1	3.3	3.1	3.2	3.5	3.3
Anti-separation property 1		-	A	A	A	A	D	C	B
Stability 1		-	A	A	A	A	A	A	B
Anti-separation property 2		-	A	A	A	A	B	B	A
Stability 2		-	A	A	A	A	A	A	A

[Table 8]

		Comp. Ex. 9	Comp. Ex. 10	Comp. Ex. 11	Comp. Ex. 12	Comp. Ex. 13	Comp. Ex. 14	Comp. Ex. 15	Comp. Ex. 16
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	-	1.0	-	-	-	-	-	-
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	-	-	1.0	-	-	-	-	-
	B2	-	-	-	1.0	-	-	-	-
	B3	-	-	-	-	1.0	-	-	-
	B6	-	-	-	-	-	1.0	-	-
	B7	-	-	-	-	-	-	1.0	-
	B8	-	-	-	-	-	-	-	1.0
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.17	0.20	0.17	0.18	0.20	0.16	0.15	0.14
Mean oil temp. 1 (°C)		96	99	94	99	102	93	94	93
Abrasion volume 1 ⁻ (mm ³)		3.2	3.2	3.3	3.7	3.6	3.4	3.3	3.2
Anti-separation property 1		A	A	A	A	A	D	C	B
Stability 1		A	A	A	A	A	A	A	B
Anti-separation property 2		A	A	A	A	A	B	B	A
Stability 2		A	A	A	A	A	A	A	A

[Table 9]

		Example 51	Example 52	Example 53	Example 54	Example 55	Example 56	Example 57	Example 58	Example 59
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	0.5	-	-	0.5	-	-	0.5	-	-
	A2	-	0.5	-	-	0.5	-	-	0.5	-
	A3	-	-	0.5	-	-	0.5	-	-	0.5
	B1	0.5	0.5	0.5	-	-	-	-	-	-
	B2	-	-	-	0.5	0.5	0.5	-	-	-
	B3	-	-	-	-	-	-	0.5	0.5	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.11	0.12	0.14	0.12	0.13	0.14	0.12	0.14	0.15
Mean oil temp. 1 (°C)		85	87	89	87	88	90	88	90	90
Abrasion volume 1 (mm ³)		3.0	3.0	3.2	3.1	3.3	3.3	3.2	3.3	3.4
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 10]

		Example 60	Example 61	Example 62	Example 63	Example 64	Example 65	Example 66	Example 67	Example 68
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	0.1	1.0	2.0	-	-	-	-	-	-
	A2	-	-	-	0.1	1.0	2.0	-	-	-
	A3	-	-	-	-	-	-	0.1	1.0	2.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.16	0.13	0.15	0.16	0.14	0.15	0.16	0.15	0.16
Mean oil temp. 1 (°C)		94	88	92	94	89	93	94	91	94
Abrasion volume 1 (mm ³)		3.4	2.8	3.0	3.4	2.9	3.0	3.4	2.9	3.1
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 11]

		Example 69	Example 70	Example 71	Example 72	Example 73	Example 74	Example 75	Example 76	Example 77
Base oil		Base oil 2	Base oil 2	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A1	0.5	0.5	0.5	-	-	0.5	-	-	0.5
	A2	-	-	-	0.5	-	-	0.5	-	-
	A3	-	-	-	-	0.5	-	-	0.5	-
	B1	-	-	0.5	0.5	0.5	-	-	-	-
	B2	-	-	-	-	-	0.5	0.5	0.5	-
	B3	-	-	-	-	-	-	-	-	0.5
	B4	0.5	-	-	-	-	-	-	-	-
	B5	-	0.5	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.14	0.17	0.12	0.13	0.14	0.13	0.15	0.15	0.13
Mean oil temp. 1 (°C)		94	94	86	87	89	87	88	90	88
Abrasion volume 1 (mm ³)		3.2	3.4	3.3	3.4	3.4	3.3	3.4	3.5	3.3
Anti-separation property 1		B	B	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 12]

	Example 78	Example 79	Example 80	Example 81	Example 82	Example 83	Example 84	Example 85	Example 86
Base oil	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A1	-	-	0.1	1.0	2.0	-	-	-
	A2	0.5	-	-	-	-	0.1	1.0	2.0
	A3	-	0.5	-	-	-	-	-	0.1
	B1	-	-	0.1	1.0	2.0	-	-	-
	B2	-	-	-	-	-	0.1	1.0	2.0
	B3	0.5	0.5	-	-	-	-	-	0.1
Refrigerant	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1	0.15	0.16	0.18	0.13	0.14	0.18	0.14	0.15	0.18
Mean oil temp. 1 (°C)	90	92	94	88	92	94	89	93	94
Abrasion volume 1 (mm ³)	3.5	3.5	3.8	3.1	3.3	3.8	3.2	3.5	3.8
Anti-separation property 1	A	A	A	A	A	A	A	A	A
Stability 1	A	A	A	A	A	A	A	A	A
Anti-separation property 2	A	A	A	A	A	A	A	A	A
Stability 2	A	A	A	A	A	A	A	A	A

[Table 13]

		Example 87	Example 88	Example 89	Example 90	Example 91	Example 92	Example 93	Example 94
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 2	Base oil 2	Base oil 5	Base oil 5
Additive (wt%)	A1	-	-	0.5	0.5	-	0.5	-	-
	A2	-	-	-	-	-	-	0.5	-
	A3	1.0	2.0	-	-	0.5	-	-	0.5
	B1	-	-	-	-	-	-	-	-
	B2	-	-	-	-	0.5	-	-	-
	B3	1.0	2.0	-	-	-	0.5	0.5	-
	B4	-	-	0.5	-	-	-	-	-
	B5	-	-	-	0.5	-	-	-	-
	C1	-	-	-	-	0.1	0.1	0.1	0.1
	C2	-	-	-	-	0.5	0.5	0.5	0.5
	C3	-	-	-	-	-	0.001	-	0.001
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.15	0.16	0.14	0.16	0.13	0.0.09	0.14	0.10
Mean oil temp. 1 (°C)		91	94	94	94	89	85	89	87
Abrasion volume 1 (mm ³)		3.3	3.7	3.8	3.8	3.2	2.6	3.4	2.7
Anti-separation property 1		A	A	B	B	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A

[Table 14]

		Example 95	Example 96	Example 97	Example 98	Example 99	Example 100
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A1	1.0	1.0	1.0	1.0	1.0	1.0
	A2	-	-	-	-	-	-
	A3	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B6	-	-	1.0	-	-	1.0
	B7	-	1.0	-	-	1.0	-
	B8	1.0	-	-	1.0	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.14	0.16	0.17	0.14	0.16	0.17
Mean oil temp. 1 (°C)		94	95	100	93	97	96
Abrasion volume 1 (mm ³)		3.0	3.1	3.2	3.5	3.3	3.4
Anti-separation property 1		B	C	D	B	C	D
Stability 1		B	A	A	B	A	A
Anti-separation property 2		A	B	B	A	B	B
Stability 2		A	A	A	A	A	A

[Table 15]

		Comp. Ex. 17	Comp. Ex. 18	Comp. Ex. 19	Comp. Ex. 20	Comp. Ex. 21	Comp. Ex. 22	Comp. Ex. 23	Comp. Ex. 24
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	-	1.0	-	-	-	-	-	-
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	-	-	1.0	-	-	-	-	-
	B2	-	-	-	1.0	-	-	-	-
	B3	-	-	-	-	1.0	-	-	-
	B6	-	-	-	-	-	1.0	-	-
	B7	-	-	-	-	-	-	-	1.0
	B8	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.18	0.19	0.17	0.18	0.20	0.16	0.15	0.13
Mean oil temp. 1 (°C)		96	99	94	99	102	93	94	93
Abrasion volume 1 (mm ³)		3.5	3.5	3.6	3.8	3.6	3.5	3.7	3.1
Anti-separation property 1		-	A	A	A	A	D	C	B
Stability 1		-	A	A	A	A	A	A	B
Anti-separation property 2		-	A	A	A	A	B	B	A
Stability 2		-	A	A	A	A	A	A	A

[Table 16]

		Comp. Ex. 25	Comp. Ex. 26	Comp. Ex. 27	Comp. Ex. 28	Comp. Ex. 29	Comp. Ex. 30	Comp. Ex. 31	Comp. Ex. 32
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A1	-	1.0	-	-	-	-	-	-
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	-	-	1.0	-	-	-	-	-
	B2	-	-	-	1.0	-	-	-	-
	B3	-	-	-	-	1.0	-	-	-
	B6	-	-	-	-	-	1.0	-	-
	B7	-	-	-	-	-	-	1.0	-
	B8	-	-	-	-	-	-	-	1.0
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.18	0.21	0.18	0.19	0.19	0.16	0.15	0.13
Mean oil temp. 1 (°C)		96	101	91	99	101	94	92	91
Abrasion volume 1 (mm ³)		3.9	3.9	4.5	4.2	4.1	3.9	3.9	4.0
Anti-separation property 1		A	A	A	A	A	D	C	D
Stability 1		A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	B	B	B
Stability 2		A	A	A	A	A	A	A	A

[Table 17]

		Example 101	Example 102	Example 103	Example 104	Example 105	Example 106	Example 107	Example 108	Example 109
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A1	0.5	-	-	0.5	-	-	0.5	-	-
	A2	-	0.5	-	-	0.5	-	-	0.5	-
	A3	-	-	0.5	-	-	0.5	-	-	0.5
	B1	0.5	0.5	0.5	-	-	-	-	-	-
	B2	-	-	-	0.5	0.5	0.5	-	-	-
	B3	-	-	-	-	-	-	0.5	0.5	0.5
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 1		0.10	0.11	0.12	0.11	0.11	0.12	0.11	0.12	0.13
Mean oil temp. 1 (°C)		84	86	87	84	85	87	84	86	87
Abrasion volume 1 (mm ³)		2.0	2.1	2.1	2.0	2.2	2.2	2.1	2.1	2.2
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 18]

		Example 110	Example 111	Example 112	Example 113	Example 114	Example 115	Example 116	Example 117	Example 118
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A1	0.1	1.0	2.0	-	-	-	-	-	-
	A2	-	-	-	0.1	1.0	2.0	-	-	-
	A3	-	-	-	-	-	-	0.1	1.0	2.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 1		0.11	0.12	0.13	0.11	0.12	0.13	0.111	0.13	0.13
Mean oil temp. 1 (°C)		86	85	88	84	86	89	85	86	89
Abrasion volume 1 (mm ³)		2.4	1.9	2.1	2.4	2.1	2.2	2.4	2.1	2.3
Anti-separation property 1		A	A	A	A	A	A	A	A	A
Stability 1		A	A	A	A	A	A	A	A	A
Anti-separation property 2		A	A	A	A	A	A	A	A	A
Stability 2		A	A	A	A	A	A	A	A	A

[Table 19]

		Example 119	Example 120	Example 121	Example 122	Example 123	Example 124	Example 125
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A1	0.5	0.5	-	0.5	1.0	1.0	1.0
	A2	-	-	-	-	-	-	-
	A3	-	-	0.5	-	-	-	-
	B1	-	-	0.5	-	-	-	-
	B2	-	-	-	0.5	-	-	-
	B3	-	-	-	-	-	-	-
	B4	0.5	-	-	-	-	-	-
	B5	-	0.5	-	-	-	-	-
	B6	-	-	-	-	-	-	1.0
	B7	-	-	-	-	-	1.0	-
	B8	-	-	-	-	1.0	-	-
	C1	-	-	0.1	0.1	-	-	-
	C2	-	-	0.5	0.5	-	-	-
	C3	-	-	-	0.001	-	-	-
Refrigerant		R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 1		0.11	0.13	0.11	0.08	0.13	0.15	0.16
Mean oil temp. 1 (°C)		89	79	86	81	91	94	94
Abrasion volume 1 (mm ³)		2.3	2.3	2.0	1.5	2.6	2.7	2.5
Anti-separation property 1		B	B	A	A	B	C	D
Stability 1		A	A	A	A	B	A	A
Anti-separation property 2		A	A	A	A	A	B	B
Stability 2		A	A	A	A	A	A	A

[Table 20]

		Comp. Ex. 45	Comp. Ex. 46	Comp. Ex. 47	Comp. Ex. 48	Comp. Ex. 49	Comp. Ex. 50	Comp. Ex. 51	Comp. Ex. 52
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A1	-	1.0	-	-	-	-	-	-
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	-	-	1.0	-	-	-	-	-
	B2	-	-	-	1.0	-	-	-	-
	B3	-	-	-	-	1.0	-	-	-
	B6	-	-	-	-	-	1.0	-	-
	B7	-	-	-	-	-	-	1.0	-
	B8	-	-	-	-	-	-	-	1.0
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 1		0.16	0.18	0.17	0.16	0.18	0.15	0.14	0.12
Mean oil temp. 1 (°C)		93	100	91	94	102	92	93	90
Abrasion volume 1 (mm ³)		2.5	2.4	3.0	2.9	3.1	2.8	3.0	2.7
Anti-separation property 1		A	A	A	A	A	D	C	B
Stability 1		A	A	A	A	A	A	A	B
Anti-separation property 2		A	A	A	A	A	B	B	A
Stability 2		A	A	A	A	A	A	A	A

[0232] [Friction property evaluation test 2]

5 The frictional coefficients of the refrigerating machine oil compositions of Examples 1, 21, 41, 43, 56, 78, 91, 93, 103 and 121 were measured using an SRV tester by Optimol Inc., between a 1/2 inch SUJ2 steel ball and an SUJ2 disc (φ10 mm). The test conditions

10 were a load of 100 N, an amplitude of 1 mm and a frequency of 25Hz, and the frictional coefficient was recorded every second from the start of the test until 20 minutes thereafter, with the average being taken as

the mean frictional coefficient (hereinafter referred to as "mean frictional coefficient 2". The refrigerant was circulated to the slide member at a flow rate of 10 L/h. The results are shown in Tables 21 and 22. In this test, the refrigerant type was selected depending on the type of base oil in the refrigerating machine oil composition. The refrigerant types used are shown in Tables 21-22.

[Table 21]

		Example 1	Example 41	Example 21	Example 43	Example 56	Example 91
Base oil		Base oil 1	Base oil 1	Base oil 3	Base oil 3	Base oil 2	Base oil 2
Additive (wt%)	A1	0.5	0.5	0.5	0.5	-	-
	A2	-	-	-	-	-	-
	A3	-	-	-	-	0.5	0.5
	B1	0.5	0.5	0.5	0.5	-	-
	B2	-	-	-	-	0.5	0.5
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	C1	-	0.1	-	0.1	-	0.1
	C2	-	0.5	-	0.5	-	0.5
	C3	-	-	-	-	-	-
	Refrigerant	R410A	R410A	R410A	R410A	R134a	R134a
Mean frictional coefficient 2		0.117	0.105	0.122	0.109	0.142	0.129

[Table 22]

		Example 78	Example 93	Example 103	Example 121
Base oil		Base oil 5	Base oil 5	Base oil 4	Base oil 4
Additive (wt%)	A1	-	-	-	-
	A2	0.5	0.5	-	-
	A3	-	-	0.5	0.5
	B1	-	-	0.5	0.5
	B2	-	-	-	-
	B3	0.5	0.5	-	-
	B4	-	-	-	-
	B5	-	-	-	-
	C1	-	0.1	-	0.1
	C2	-	0.5	-	0.5
	C3	-	-	-	-
Refrigerant		R134a	R134a	R22	R22
Mean frictional coefficient 2		0.149	0.141	0.122	0.109

[0233] [Examples 126-452, Comparative Examples 53-
5 100]

Refrigerating machine oil compositions having the
compositions shown in Tables 23-74 were prepared using
the following base oils and additives, for Examples
126-452 and Comparative Examples 53-100.

10 [0234] (Base oil)

Base oil 1: Tetraester of pentaerythritol and an
equimolar mixture of 2-ethylhexanoic acid and 3,5,5-
trimethylhexanoic acid (kinematic viscosity at 40°C:
68.5 mm²/s, pour point: -25°C)

15 Base oil 2: Diester of 1,2-cyclohexanedicarboxylic
acid and 2-ethylhexanol (kinematic viscosity at 40°C:
15 mm²/s, pour point: -40°C)

Base oil 3: Random copolymer of vinyl ethyl ether and vinyl isobutyl ether (vinyl ethyl ether/vinyl isobutyl ether molar ratio: 7/1, number average molecular weight: 900, kinematic viscosity at 40°C: 68.5 mm²/s, kinematic viscosity at 100°C: 8 mm²/s, pour point: -40°C)

Base oil 4: Naphthene-based mineral oil (kinematic viscosity at 40°C: 56.6 mm²/s, pour point: -30°C)

Base oil 5: Polypropyleneglycol monomethylether (number average molecular weight: 1000, kinematic viscosity at 40°C: 46 mm²/s, kinematic viscosity at 100°C: 10 mm²/s, pour point: -40°C).

Base oil 6: Complete ester of a mixture of dipentaerythritol and pentaerythritol (molar ratio = 1:1) with a mixture of 2-ethylhexanoic acid and 3,5,5-trimethylhexanoic acid (molar ratio = 1:1) (kinematic viscosity at 40°C: 195 mm²/s, pour point: -30°C)

Base oil 7: Paraffin-based mineral oil (kinematic viscosity at 40°C: 92 mm²/s, pour point: -15°C)

Base oil 8: Paraffin-based mineral oil (kinematic viscosity at 40°C: 12 mm²/s, pour point: -30°C).

[0235] (Phosphorus-based extreme pressure agent)

A4: Triphenyl phosphorothionate

A5: Tricresyl phosphorothionate

A6: Tri(n-octyl) phosphorothionate.

[0236] (Oil agent)

B1: Butyl stearate

B2: Diisobutyl adipate

B3: Diisodecyl adipate

B4: Glycerin monooleate

5 B5: Glycerin trioleate

B6: Oleyl alcohol

B7: 2-Ethylhexyl glyceryl ether

B8: Stearic acid.

[0237] (Other additives)

10 C1: Di-t-butyl-p-cresol

C2: Glycidyl-2,2'-dimethyl octanoate

C3: Benzotriazole.

[0238] [Friction property and abrasion property
evaluation test 3]

15 Each of the refrigerating machine oil compositions
of Examples 126-452 and Comparative Examples 41-100
were subjected to the evaluation tests described below.
The row "Refrigerant" in Tables 23-74 shows the type of
refrigerant used in the friction property and abrasion
property evaluation test.

20

[0239] A FALEX test (ASTM D2670) was conducted under
the following conditions while blowing the refrigerant
into the refrigerating machine oil composition.

Test initial temperature: 25°C

25 Test time: 30 min

Load: 1334 N

Refrigerant blow-in rate: 10 L/h

[0240] The frictional coefficient and oil temperature were measured every other second after the start of the FALEX test, and the mean values were calculated (hereinafter referred to as "mean frictional coefficient 3" and "mean oil temperature 3"). The weights of the pin and block were measured after completion of the test, and the abrasion loss was determined in terms of weight reduction (hereinafter referred to as "abrasion loss 3"). The results are shown in Tables 23-74.

[Table 23]

		Example 126	Example 127	Example 128	Example 129	Example 130	Example 131	Example 132	Example 133
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
		0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	-	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.101	0.102	0.103	0.102	0.113	0.111	0.108	0.109
Mean oil temp. 3 (°C)		45	45	46	46	47	52	51	51
Abrasion loss 3 (mg)		7.8	7.5	7.9	8.4	8.6	8.5	8.8	8.8

[Table 24]

		Example 134	Example 135	Example 136	Example 137	Example 138	Example 139	Example 140	Example 141
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.101	0.101	0.102	0.103	0.114	0.113	0.109	0.110
Mean oil temp. 3 (°C)		44	45	45	44	46	50	52	51
Abrasion loss 3 (mg)		7.4	7.6	7.2	8.5	8.6	8.9	8.6	9.2

[Table 25]

		Example 142	Example 143	Example 144	Example 145	Example 146	Example 147	Example 148	Example 149
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	-	-	-	-	-	-	-	-
	A6	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	-	0.5
	B8	-	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.102	0.103	0.103	0.102	0.114	0.112	0.109	0.110
Mean oil temp. 3 (°C)		49	44	44	43	43	52	52	51
Abrasion loss 3 (mg)		7.8	7.9	7.9	8.5	8.6	8.6	8.5	8.6

[Table 26]

		Example 150	Example 151	Example 152	Example 153	Example 154	Example 155	Example 156	Example 157	Example 158
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	0.01	0.3	0.10	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
	B4	-	-	-	-	-	-	-	-	-
	B5	-	-	-	-	-	-	-	-	-
	B6	-	-	-	-	-	-	-	-	-
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.113	0.104	0.106	0.111	0.104	0.106	0.110	0.102	0.105
Mean oil temp. 3 (°C)		48	46	48	46	46	48	48	46	49
Abrasion loss 3 (mg)		12.2	7.2	8.0	12.1	7.5	7.9	12.3	7.7	8.4

[Table 27]

		Example 159	Example 160	Example 161	Example 162	Example 163	Example 164	Example 165	Example 166	Example 167
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	-	-	-	-	-	-	-	-	-
	B2	-	-	-	-	-	-	-	-	-
	B3	-	-	-	-	-	-	-	-	-
	B4	0.1	1.0	2.0	-	-	-	-	-	-
	B5	-	-	-	0.1	1.0	2.0	-	-	-
	B6	-	-	-	-	-	-	0.1	1.0	2.0
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.112	0.100	0.105	0.110	0.112	0.113	0.118	0.113	0.115
Mean oil temp. 3 (°C)		48	46	49	50	46	47	52	50	52
Abrasion loss 3 (mg)		12.2	8.5	8.8	12.1	8.6	8.7	12.2	8.4	8.6

[Table 28]

		Example 168	Example 169	Example 170	Example 171	Example 172	Example 173
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-
	A5	-	-	-	0.01	0.3	1.0
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	0.1	1.0	2.0	-	-	-
	B8	-	-	-	0.1	1.0	2.0
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.114	0.110	0.112	0.117	0.111	0.112
Mean oil temp. 3 (°C)		53	51	51	52	51	51
Abrasion loss 3 (mg)		12.0	9.2	9.0	11.8	9.1	9.2

[Table 29]

		Example 174	Example 175	Example 176	Example 177	Example 178	Example 179	Example 180
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	0.5	-
	B2	-	-	-	-	-	-	-
	B3	-	0.5	-	-	-	-	-
	B4	-	-	-	-	-	-	-
	B5	-	-	0.5	-	-	-	0.5
	B6	-	-	-	-	-	-	-
	B7	-	-	-	0.5	-	-	-
	B8	-	-	-	-	0.5	-	-
	C1	-	-	-	-	-	0.1	0.1
	C2	-	-	-	-	-	0.5	0.5
	C3	0.001	0.002	0.005	0.0005	0.001	0.001	0.001
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.091	0.088	0.101	0.102	0.104	0.091	0.091
Mean oil temp. 3 (°C)		41	40	41	46	47	41	43
Abrasion loss 3 (mg)		7.5	7.3	7.2	8.3	8.2	7.6	7.3

[Table 30]

		Comp. Ex. 41	Comp. Ex. 42	Comp. Ex. 43	Comp. Ex. 44	Comp. Ex. 45	Comp. Ex. 46
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	0.5	-	-	-	-	-
	A5	-	0.5	-	-	-	-
	A6	-	-	0.5	-	-	-
	B1	-	-	-	0.5	-	-
	B2	-	-	-	-	0.5	-
	B3	-	-	-	-	-	0.5
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	-	-	-	-	-	-
	B8	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.128	0.135	0.129	0.115	0.113	0.112
Mean oil temp. 3 (°C)		60	62	59	54	54	53
Abrasion loss 3 (mg)		9.4	9.5	9.9	12.8	13.1	12.9

[Table 31]

		Comp. Ex. 47	Comp. Ex. 48	Comp. Ex. 49	Comp. Ex. 50	Comp. Ex. 51	Comp. Ex. 52
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A4	-	-	-	-	-	-
	A5	-	-	-	-	-	-
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	0.5	-	-	-	-	-
	B5	-	0.5	-	-	-	-
	B6	-	-	0.5	-	-	-
	B7	-	-	-	0.5	-	-
	B8	-	-	-	-	0.5	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.110	0.117	0.118	0.108	0.109	0.125
Mean oil temp. 3 (°C)		52	54	58	56	57	58
Abrasion loss 3 (mg)		12.9	13.1	13.3	12.8	13.5	12.5

[Table 32]

		Example 181	Example 182	Example 183	Example 184	Example 185	Example 186	Example 187	Example 188
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.105	0.107	0.108	0.106	0.117	0.118	0.112	0.111
Mean oil temp. 3 (°C)		45	46	46	47	13	48	49	50
Abrasion loss 3 (mg)		8.8	8.6	8.9	9.4	9.6	9.5	9.8	9.9

[Table 33]

		Example 189	Example 190	Example 191	Example 192	Example 193	Example 194	Example 195	Example 196
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	-	0.5	-
	B7	-	-	-	-	-	-	-	0.5
	B8	-	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.106	0.107	0.108	0.107	0.115	0.117	0.113	0.112
Mean oil temp. 3 (°C)		46	46	48	47	46	50	48	49
Abrasion loss 3 (mg)		8.7	8.7	8.8	9.5	9.8	9.6	9.7	9.6

[Table 34]

		Example 197	Example 198	Example 199	Example 200	Example 201	Example 202	Example 203	Example 204
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	-	-	-	-	-	-	-	-
	A6	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.108	0.106	0.108	0.107	0.116	0.119	0.113	0.112
Mean oil temp. 3 (°C)		46	47	46	46	47	51	51	50
Abrasion loss 3 (mg)		8.7	8.6	8.8	9.5	9.7	9.7	9.6	9.8

[Table 35]

		Example 205	Example 206	Example 207	Example 208	Example 209	Example 210	Example 211	Example 212	Example 213
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	0.01	0.3	0.10	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
	B4	-	-	-	-	-	-	-	-	-
	B5	-	-	-	-	-	-	-	-	-
	B6	-	-	-	-	-	-	-	-	-
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.116	0.107	0.108	0.117	0.107	0.108	0.115	0.108	0.110
Mean oil temp. 3 (°C)		48	46	47	49	47	48	48	46	48
Abrasion loss 3 (mg)		12.2	8.7	8.7	12.4	8.6	8.8	12.1	8.6	8.8

[Table 36]

		Example 214	Example 215	Example 216	Example 217	Example 218	Example 219	Example 220	Example 221	Example 222
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	-	-	-	-	-	-	-	-	-
	B2	-	-	-	-	-	-	-	-	-
	B3	-	-	-	-	-	-	-	-	-
	B4	0.1	1.0	2.0	-	-	-	-	-	-
	B5	-	-	-	0.1	1.0	2.0	-	-	-
	B6	-	-	-	-	-	-	0.1	1.0	2.0
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient ³		0.113	0.107	0.108	0.117	0.117	0.118	0.122	0.116	0.115
Mean oil temp. ³ (°C)		48	46	48	49	47	48	52	51	50
Abrasion loss ³ (mg)		12.5	9.5	9.6	12.6	9.6	9.7	12.3	9.5	9.4

[Table 37]

		Example 223	Example 224	Example 225	Example 226	Example 227	Example 228
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-
	A5	-	-	-	0.01	0.3	1.0
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	0.1	1.0	2.0	-	-	-
	B8	-	-	-	0.1	1.0	2.0
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.115	0.114	0.115	0.119	0.113	0.114
Mean oil temp. 3 (°C)		50	48	49	50	48	48
Abrasion loss 3 (mg)		12.8	9.5	9.7	12.7	9.7	9.9

[Table 38]

		Example 229	Example 230	Example 231	Example 232	Example 234	Example 235	Example 236
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-
	B2	-	-	-	-	-	-	-
	B3	-	0.5	-	-	-	0.5	-
	B4	-	-	-	-	-	-	-
	B5	-	-	0.5	-	-	-	-
	B6	-	-	-	-	-	-	-
	B7	-	-	-	0.5	-	-	0.5
	B8	-	-	-	-	0.5	-	-
	C1	-	-	-	-	-	0.1	0.1
	C2	-	-	-	-	-	0.5	0.5
	C3	0.001	0.002	0.005	0.0005	0.001	0.002	0.0005
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.094	0.093	0.103	0.103	0.102	0.094	0.103
Mean oil temp. 3 (°C)		41	43	44	49	49	41	47
Abrasion loss 3 (mg)		8.0	7.9	8.0	9.2	9.3	8.0	8.8

[Table 39]

		Comp. Ex. 53	Comp. Ex. 54	Comp. Ex. 55	Comp. Ex. 56	Comp. Ex. 57	Comp. Ex. 58
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	0.5	-	-	-	-	-
	A5	-	0.5	-	-	-	-
	A6	-	-	0.5	-	-	-
	B1	-	-	-	0.5	-	-
	B2	-	-	-	-	0.5	-
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	-	-	-	-	-	-
	B8	-	-	-	-	-	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.131	0.132	0.135	0.118	0.119	0.117
Mean oil temp. 3 (°C)		59	60	61	53	54	54
Abrasion loss 3 (mg)		9.8	10.2	10.5	14.8	15.3	15.1

[Table 40]

		Comp. Ex. 59	Comp. Ex. 60	Comp. Ex. 61	Comp. Ex. 62	Comp. Ex. 63	Comp. Ex. 64
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A4	-	-	-	-	-	-
	A5	-	-	-	-	-	-
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	0.5	-	-	-	-	-
	B5	-	0.5	-	-	-	-
	B6	-	-	0.5	-	-	-
	B7	-	-	-	0.5	-	-
	B8	-	-	-	-	0.5	-
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 3		0.115	0.119	0.125	0.117	0.118	0.128
Mean oil temp. 3 (°C)		53	54	56	53	55	55
Abrasion loss 3 (mg)		14.9	15.1	15.2	15.5	15.1	14.2

[Table 41]

		Example 236	Example 237	Example 238	Example 239	Example 240	Example 241	Example 242	Example 243
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	-	0.5
	B8	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.105	0.109	0.110	0.108	0.121	0.125	0.117	0.116
Mean oil temp. 3 (°C)		47	49	48	48	49	54	52	53
Abrasion loss 3 (mg)		8.1	8.9	8.8	9.3	9.5	9.6	9.5	9.6

[Table 42]

		Example 244	Example 245	Example 246	Example 247	Example 248	Example 249	Example 250	Example 251
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.108	0.109	0.108	0.109	0.122	0.125	0.118	0.117
Mean oil temp. 3 (°C)		48	48	47	49	49	53	55	54
Abrasion loss 3 (mg)		8.9	8.8	8.7	9.4	9.6	9.4	9.3	9.5

[Table 43]

		Example 252	Example 253	Example 254	Example 255	Example 256	Example 257	Example 258	Example 259
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	-	-	-	-	-	-	-	-
	A6	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	-	0.5
	B8	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.108	0.107	0.109	0.107	0.122	0.125	0.118	0.117
Mean oil temp. 3 (°C)		48	48	49	47	49	54	55	53
Abrasion loss 3 (mg)		8.8	8.7	8.9	9.5	9.6	9.5	9.6	9.4

{Table 44}

		Example 260	Example 261	Example 262	Example 263	Example 264	Example 265	Example 266	Example 267	Example 268
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	0.01	0.3	0.10	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
	B4	-	-	-	-	-	-	-	-	-
	B5	-	-	-	-	-	-	-	-	-
	B6	-	-	-	-	-	-	-	-	-
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient ³		0.113	0.106	0.107	0.109	0.108	0.110	0.111	0.108	0.109
Mean oil temp. ³ (°C)		49	47	47	50	49	50	52	50	51
Abrasion loss ³ (mg)		12.9	8.0	8.1	12.8	8.9	8.8	12.9	8.9	9.0

[Table 45]

		Example 269	Example 270	Example 271	Example 272	Example 273	Example 274	Example 275	Example 276	Example 277
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	-	0.01	0.3	1.0
	A6	-	-	-	-	-	-	-	-	-
	B1	-	-	-	-	-	-	-	-	-
	B2	-	-	-	-	-	-	-	-	-
	B3	-	-	-	-	-	-	-	-	-
	B4	0.1	1.0	2.0	-	-	-	-	-	-
	B5	-	-	-	0.1	1.0	2.0	-	-	-
	B6	-	-	-	-	-	-	0.1	1.0	2.0
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.111	0.109	0.108	0.117	0.122	0.123	0.118	0.120	0.124
Mean oil temp. 3 (°C)		51	49	49	52	48	49	54	53	53
Abrasion loss 3 (mg)		12.7	9.7	9.8	12.9	9.7	9.9	13.0	9.1	9.0

[Table 46]

		Example 278	Example 279	Example 280	Example 281	Example 282	Example 283
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-
	A5	-	-	-	0.01	0.3	1.0
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	0.1	1.0	2.0	-	-	-
	B8	-	-	-	0.1	1.0	2.0
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3-		0.119	0.114	0.115	0.118	0.118	0.120
Mean oil temp. 3 (°C)		54	53	52	54	53	53
Abrasion loss 3 (mg)		12.8	9.2	9.5	12.7	9.6	9.8

[Table 47]

		Example 284	Example 285	Example 286	Example 287	Example 288	Example 289	Example 290
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	0.5	-
	B2	-	-	-	-	-	-	-
	B3	-	0.5	-	-	-	-	-
	B4	-	-	-	-	-	-	-
	B5	-	-	0.5	-	-	-	-
	B6	-	-	-	-	-	-	-
	B7	-	-	-	0.5	-	-	-
	B8	-	-	-	-	0.5	-	0.5
	B8	-	-	-	-	-	0.1	0.1
	C1	-	-	-	-	-	0.5	0.5
	C2	-	-	-	-	-	-	-
	C3	0.001	0.002	0.005	0.0005	0.001	0.001	0.001
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.099	0.101	0.110	0.112	0.111	0.100	0.111
Mean oil temp. 3 (°C)		45	46	46	49	48	45	48
Abrasion loss 3 (mg)		7.7	8.0	8.2	8.5	8.7	7.8	8.8

[Table 48]

		Comp. Ex. 65	Comp. Ex. 66	Comp. Ex. 67	Comp. Ex. 68	Comp. Ex. 69	Comp. Ex. 70
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	0.5	-	-	-	-	-
	A5	-	0.5	-	-	-	-
	A6	-	-	0.5	-	-	-
	B1	-	-	-	0.5	-	-
	B2	-	-	-	-	0.5	-
	B3	-	-	-	-	-	0.5
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	-	-	-	-	-	-
	B8	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.132	0.139	0.133	0.115	0.111	0.113
Mean oil temp. 3 (°C)		61	50	58	55	54	55
Abrasion loss 3 (mg)		9.3	9.5	9.9	14.9	13.9	14.1

[Table 49]

		Comp. Ex. 71	Comp. Ex. 72	Comp. Ex. 73	Comp. Ex. 74	Comp. Ex. 75	Comp. Ex. 76
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A4	-	-	-	-	-	-
	A5	-	-	-	-	-	-
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	0.5	-	-	-	-	-
	B5	-	0.5	-	-	-	-
	B6	-	-	0.5	-	-	-
	B7	-	-	-	0.5	-	-
	B8	-	-	-	-	0.5	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.113	0.119	0.120	0.115	0.116	0.130
Mean oil temp. 3 (°C)		54	55	57	55	56	60
Abrasion loss 3 (mg)		13.7	14.5	14.8	14.4	15.4	13.5

[Table 50]

		Example 291	Example 292	Example 293	Example 294	Example 295	Example 296	Example 297	Example 298
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.108	0.110	0.109	0.109	0.119	0.120	0.113	0.114
Mean oil temp. 3 (°C)		44	46	45	45	46	52	53	50
Abrasion loss 3 (mg)		10.1	10.3	10.6	10.9	11.1	11.0	10.9	10.4

[Table 51]

		Example 299	Example 300	Example 301	Example 302	Example 303	Example 304	Example 305	Example 306
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient ³		0.111	0.109	0.111	0.110	0.121	0.120	0.114	0.115
Mean oil temp. (°C)		46	46	46	45	44	52	53	52
Abrasion loss ³ (mg)		10.7	10.8	10.6	11.0	11.2	11.2	11.1	11.2

[Table 52]

		Example 307	Example 308	Example 309	Example 310	Example 311	Example 312	Example 313	Example 314
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	-	-	-	-	-	-	-	-
	A6	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.109	0.110	0.110	0.111	0.121	0.121	0.114	0.115
Mean oil temp. 3 (°C)		47	46	47	46	45	53	51	51
Abrasion loss 3 (mg)		10.4	10.3	10.8	11.1	11.3	11.0	11.1	11.0

[Table 53]

		Example 315	Example 316	Example 317	Example 318	Example 319	Example 320	Example 321	Example 322	Example 323
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	0.01	0.3	0.10	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
	B4	-	-	-	-	-	-	-	-	-
	B5	-	-	-	-	-	-	-	-	-
	B6	-	-	-	-	-	-	-	-	-
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient ³		0.114	0.109	0.110	0.114	0.109	0.109	0.116	0.109	0.110
Mean oil temp. ³ (°C)		47	45	46	48	46	47	48	48	46
Abrasion loss ³ (mg)		12.7	9.9	9.8	13.1	10.6	10.7	13.0	10.6	10.2

[Table 54]

		Example 324	Example 325	Example 326	Example 327	Example 328	Example 329	Example 330	Example 331	Example 332
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	-	-	-	-	-	-	-	-	-
	B2	-	-	-	-	-	-	-	-	-
	B3	-	-	-	-	-	-	-	-	-
	B4	0.1	1.0	2.0	-	-	-	-	-	-
	B5	-	-	-	0.1	1.0	2.0	-	-	-
	B6	-	-	-	-	-	-	0.1	1.0	2.0
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.115	0.109	0.110	0.123	0.118	0.118	0.122	0.120	0.120
Mean oil temp. 3 (°C)		48	46	47	46	44	45	55	53	54
Abrasion loss 3 (mg)		13.1	11.2	11.3	12.9	11.3	11.5	13.2	11.3	11.4

[Table 55]

		Example 333	Example 334	Example 335	Example 336	Example 337	Example 338
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-
	A5	-	-	-	0.01	0.3	1.0
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	0.1	1.0	2.0	-	-	-
	B8	-	-	-	0.1	1.0	2.0
	C1	-	-	-	-	-	-
	C2	-	-	-	-	-	-
	C3	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.118	0.112	0.114	0.118	0.114	0.115
Mean oil temp. 3 (°C)		54	53	54	54	52	53
Abrasion loss 3 (mg)		12.8	11.0	11.2	13.0	11.2	11.4

[Table 56]

		Example 339	Example 340	Example 341	Example 342	Example 343	Example 344	Example 345
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	0.5	-
	B2	-	-	-	-	-	-	-
	B3	-	0.5	-	-	-	-	-
	B4	-	-	-	-	-	-	-
	B5	-	-	0.5	-	-	-	-
	B6	-	-	-	-	-	-	-
	B7	-	-	-	0.5	-	-	-
	B8	-	-	-	-	0.5	-	0.5
	C1	-	-	-	-	-	0.1	0.1
	C2	-	-	-	-	-	0.5	0.5
	C3	0.001	0.002	0.005	0.0005	0.001	0.001	0.001
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.100	0.101	0.110	0.115	0.116	0.100	0.116
Mean oil temp. 3 (°C)		43	45	42	51	50	44	52
Abrasion loss 3 (mg)		9.3	9.5	9.1	10.1	10.1	9.3	10.2

[Table 57]

		Comp. Ex. 77	Comp. Ex. 78	Comp. Ex. 79	Comp. Ex. 80	Comp. Ex. 81	Comp. Ex. 82
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	0.5	-	-	-	-	-
	A5	-	0.5	-	-	-	-
	A6	-	-	0.5	-	-	-
	B1	-	-	-	0.5	-	-
	B2	-	-	-	-	0.5	-
	B3	-	-	-	-	-	0.5
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	-	-	-	-	-	-
	B8	-	-	-	-	-	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.128	0.129	0.132	0.116	0.116	0.118
Mean oil temp. 3 (°C)		57	59	59	52	52	53
Abrasion loss 3 (mg)		11.1	11.3	11.4	14.3	14.8	14.9

[Table 58]

		Comp. Ex. 83	Comp. Ex. 84	Comp. Ex. 85	Comp. Ex. 86	Comp. Ex. 87	Comp. Ex. 88
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A4	-	-	-	-	-	-
	A5	-	-	-	-	-	-
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	0.5	-	-	-	-	-
	B5	-	0.5	-	-	-	-
	B6	-	-	0.5	-	-	-
	B7	-	-	-	0.5	-	-
	B8	-	-	-	-	0.5	-
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 3		0.117	0.125	0.125	0.120	0.121	0.126
Mean oil temp. 3 (°C)		52	53	57	55	55	55
Abrasion loss 3 (mg)		15.2	14.5	14.9	14.7	14.5	13.5

[Table 59]

		Example 346	Example 347	Example 348	Example 349	Example 350	Example 351	Example 352	Example 353
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.112	0.112	0.113	0.112	0.123	0.121	0.116	0.117
Mean oil temp. 3 (°C)		47	47	49	48	47	54	53	55
Abrasion loss 3 (mg)		8.1	8.3	8.0	8.7	8.8	8.8	8.9	8.9

[Table 60]

		Example 354	Example 355	Example 356	Example 357	Example 358	Example 359	Example 360	Example 361
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A6	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.111	0.112	0.114	0.110	0.124	0.123	0.116	0.117
Mean oil temp. 3 (°C)		48	47	48	48	47	55	54	54
Abrasion loss 3 (mg)		7.9	7.8	8.1	8.9	9.0	9.1	9.0	9.0

[Table 61]

		Example 362	Example 363	Example 364	Example 365	Example 366	Example 367	Example 368	Example 369
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	-	-	-	-	-	-	-	-
	A5	-	-	-	-	-	-	-	-
	A6	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	-	0.5
	B8	-	-	-	-	-	-	-	-
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.112	0.113	0.111	0.114	0.124	0.123	0.117	0.117
Mean oil temp. 3 (°C)		48	47	47	48	48	54	53	55
Abrasion loss 3 (mg)		8.0	7.9	7.8	9.1	9.0	9.0	8.9	9.1

[Table 62]

		Example 370	Example 371	Example 372	Example 373	Example 374	Example 375	Example 376	Example 377	Example 378
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	0.01	0.3	0.10	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	0.1	1.0	2.0	-	-	-	-	-	-
	B2	-	-	-	0.1	1.0	2.0	-	-	-
	B3	-	-	-	-	-	-	0.1	1.0	2.0
	B4	-	-	-	-	-	-	-	-	-
	B5	-	-	-	-	-	-	-	-	-
	B6	-	-	-	-	-	-	-	-	-
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient ³		0.119	0.111	0.113	0.121	0.111	0.112	0.120	0.110	0.111
Mean oil temp. ³ (°C)		50	47	49	48	46	47	49	48	49
Abrasion loss ³ (mg)		9.4	8.4	8.2	9.3	7.8	8.0	9.4	7.7	7.9

[Table 63]

		Example 379	Example 380	Example 381	Example 382	Example 383	Example 384	Example 385	Example 386	Example 387
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-	-	-	-
	A5	-	-	-	0.01	0.3	1.0	-	-	-
	A6	-	-	-	-	-	-	0.01	0.3	1.0
	B1	-	-	-	-	-	-	-	-	-
	B2	-	-	-	-	-	-	-	-	-
	B3	-	-	-	-	-	-	-	-	-
	B4	0.1	1.0	2.0	-	-	-	-	-	-
	B5	-	-	-	0.1	1.0	2.0	-	-	-
	B6	-	-	-	-	-	-	0.1	1.0	2.0
	B7	-	-	-	-	-	-	-	-	-
	B8	-	-	-	-	-	-	-	-	-
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient ³		0.121	0.111	0.112	0.124	0.122	0.122	0.124	0.122	0.122
Mean oil temp. ³ (°C)		50	48	49	48	47	48	54	52	52
Abrasion loss ³ (mg)		9.3	8.8	8.7	9.4	8.9	9.0	9.3	8.6	8.6

[Table 64]

		Example 388	Example 389	Example 390	Example 391	Example 392	Example 393
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	0.01	0.3	1.0	-	-	-
	A5	-	-	-	0.01	0.3	1.0
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	0.1	1.0	2.0	-	-	-
	B8	-	-	-	0.1	1.0	2.0
Refrigerant		R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.125	0.115	0.117	0.127	0.116	0.117
Mean oil temp. 3 (°C)		53	52	51	53	51	51
Abrasion loss 3 (mg)		9.4	8.8	9.0	9.4	8.9	9.2

[Table 65]

		Example 394	Example 395	Example 396	Example 397	Example 398	Example 399	Example 400
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A5	-	-	-	-	-	-	-
	A6	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	0.5	-
	B2	-	-	-	-	-	-	-
	B3	-	0.5	-	-	-	-	-
	B4	-	-	-	-	-	-	-
	B5	-	-	0.5	-	-	-	0.5
	B6	-	-	-	-	-	-	-
	B7	-	-	-	0.5	-	-	-
	B8	-	-	-	-	0.5	-	0.5
	C1	-	-	-	-	-	0.1	0.1
	C2	-	-	-	-	-	0.5	0.5
	C3	0.001	0.002	0.005	0.0005	0.001	0.001	0.005
Refrigerant		R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.102	0.105	0.110	0.117	0.118	0.102	0.110
Mean oil temp. 3 (°C)		45	44	45	51	50	46	45
Abrasion loss 3 (mg)		7.6	7.9	7.7	8.1	8.2	7.6	7.8

[Table 66]

		Comp. Ex. 89	Comp. Ex. 90	Comp. Ex. 91	Comp. Ex. 92	Comp. Ex. 93	Comp. Ex. 94
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	0.5	-	-	-	-	-
	A5	-	0.5	-	-	-	-
	A6	-	-	0.5	-	-	-
	B1	-	-	-	0.5	-	-
	B2	-	-	-	-	0.5	-
	B3	-	-	-	-	-	0.5
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	-	-	-	-	-	-
	B8	-	-	-	-	-	-
Refrigerant		R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.133	0.135	0.137	0.121	0.123	0.122
Mean oil temp. 3 (°C)		61	63	62	53	55	54
Abrasion loss 3 (mg)		8.8	8.7	8.9	10.5	10.8	10.9

[Table 67]

		Comp. Ex. 95	Comp. Ex. 96	Comp. Ex. 97	Comp. Ex. 98	Comp. Ex. 99	Comp. Ex. 100
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A4	-	-	-	-	-	-
	A5	-	-	-	-	-	-
	A6	-	-	-	-	-	-
	B1	-	-	-	-	-	-
	B2	-	-	-	-	-	-
	B3	-	-	-	-	-	-
	B4	0.5	-	-	-	-	-
	B5	-	0.5	-	-	-	-
	B6	-	-	0.5	-	-	-
	B7	-	-	-	0.5	-	-
	B8	-	-	-	-	0.5	-
Refrigerant		R22	R22	R22	R22	R22	R22
Mean frictional coefficient 3		0.112	0.115	0.116	0.116	0.117	0.134
Mean oil temp. 3 (°C)		52	53	55	56	56	57
Abrasion loss 3 (mg)		11.1	10.7	10.8	10.9	11.3	10.2

[Table 68]

		Example 401	Example 402	Example 403	Example 404	Example 405	Example 406	Example 407	Example 408
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R407C	R407C	R407C	R407C	R407C	R407C	R407C	R407C
Mean frictional coefficient 3		0.102	0.102	0.104	0.103	0.114	0.112	0.108	0.111
Mean oil temp. 3 (°C)		45	45	47	46	48	51	52	52
Abrasion loss 3 (mg)		7.6	7.7	8.0	8.3	8.7	8.4	8.7	8.6

[Table 69]

		Example 405	Example 406	Example 407	Example 408	Example 409	Example 410	Example 411	Example 412
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R407C	R407C	R407C	R407C	R407C	R407C	R407C	R407C
Mean frictional coefficient 3		0.106	0.106	0.107	0.107	0.115	0.117	0.113	0.113
Mean oil temp. 3 (°C)		45	46	47	46	47	47	50	51
Abrasion loss 3 (mg)		8.6	8.7	8.9	9.2	9.7	9.6	9.7	9.7

[Table 70]

		Example 413	Example 414	Example 415	Example 416	Example 417	Example 418	Example 419	Example 420
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂
Mean frictional coefficient 3		0.103	0.107	0.111	0.110	0.120	0.124	0.115	0.114
Mean oil temp. 3 (°C)		48	50	49	49	50	54	53	55
Abrasion loss 3 (mg)		8.3	9.1	8.9	9.4	9.6	9.6	9.5	9.7

[Table 71]

		Example 421	Example 422	Example 423	Example 424	Example 425	Example 426	Example 427	Example 428
Base oil		Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂
Mean frictional coefficient 3		0.111	0.112	0.113	0.114	0.124	0.123	0.119	0.120
Mean oil temp. 3 (°C)		47	46	48	48	50	53	53	54
Abrasion loss 3 (mg)		8.1	7.8	8.2	8.7	8.9	8.7	8.9	8.9

[Table 72]

		Example 429	Example 430	Example 431	Example 432	Example 433	Example 434	Example 435	Example 436
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂
Mean frictional coefficient 3		0.106	0.108	0.110	0.110	0.119	0.121	0.116	0.117
Mean oil temp. 3 (°C)		46	46	47	48	48	49	51	52
Abrasion loss 3 (mg)		9.3	9.1	9.2	9.7	9.8	9.7	10.0	10.2

[Table 73]

		Example 437	Example 438	Example 439	Example 440	Example 441	Example 442	Example 443	Example 444
Base oil		Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R290	R290	R290	R290	R290	R290	R290	R290
Mean frictional coefficient 3		0.093	0.094	0.094	0.095	0.103	0.101	0.099	0.101
Mean oil temp. 3 (°C)		44	44	46	45	47	49	50	50
Abrasion loss 3 (mg)		7.6	7.7	8.0	8.3	8.4	8.3	8.5	8.6

[Table 74]

		Example 445	Example 446	Example 447	Example 448	Example 449	Example 450	Example 451	Example 452
Base oil		Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R600a	R600a	R600a	R600a	R600a	R600a	R600a	R600a
Mean frictional coefficient 3		0.105	0.108	0.109	0.107	0.123	0.121	0.119	0.118
Mean oil temp. 3 (°C)		48	49	50	50	51	53	55	54
Abrasion loss 3 (mg)		7.8	7.5	7.9	8.4	8.6	8.5	8.8	8.8

[0241] The refrigerating machine oil compositions of Examples 126-133, Examples 181-188, Examples 236-243, Examples 291-298 and Examples 346-353 were subjected to the following evaluation tests. The row "Refrigerant" in Tables 46-50 shows the type of refrigerant used in the evaluation tests.

[0242] [Anti-separation property test 2]

First, base oils 1-5 were used to prepare test solutions comprising 20 vol% of each base oil and 80 vol% of refrigerant, and the bilayer separation temperature of the base oil and refrigerant was measured. The obtained results were as follows.

Base oil 1 and R410A: 10°C

Base oil 2 and R134a: -35°C

Base oil 3 and R410A: -50°C

Base oil 4 and R22: -8°C

Base oil 5 and R134a: -45°C.

5 [0243] An anti-separation property evaluation test was then conducted according to JIS K 2211. Specifically, a test solution was prepared comprising 20 vol% of the refrigerating machine oil composition and 80 vol% of refrigerant, the test solution was
10 cooled to a temperature of 5°C higher than the bilayer separation temperature of the base oil in the composition, the outer appearance of the composition was visually observed, and the anti-separation property was evaluated based on the following scale.
15 The results are shown in Tables 75-79.

A: Transparent

B: Slight cloudiness

C: Completely opaque

D: Separation of additives

20 [0244] [Stability evaluation test 2]

A shielded glass tube test was carried out according to JIS K 2211 using iron, copper and aluminum as catalysts, and the presence of sludge was observed
25 after a period of 2 weeks at 175°C. The results are shown in Tables 75-79. Letter A in the tables

indicates that no sludge was found, B indicates that a very small amount of sludge was found, and C indicates that a large amount of sludge was found.

5

[Table 75]

		Example 126	Example 127	Example 128	Example 129	Example 130	Example 131	Example 132	Example 133
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Anti-separation property 2		A	A	A	B	B	B	B	A
Stability 2		A	A	A	A	A	A	A	B

[Table 76]

		Example 181	Example 182	Example 183	Example 184	Example 185	Example 186	Example 187	Example 188
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Anti-separation property 2		A	A	A	B	B	B	B	A
Stability 2		A	A	A	A	A	A	A	B

[Table 77]

		Example 236	Example 237	Example 238	Example 239	Example 240	Example 241	Example 242	Example 243
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Anti-separation property 2		A	A	A	B	B	B	B	A
Stability 2		A	A	A	A	A	A	A	B

[Table 78]

		Example 291	Example 292	Example 293	Example 294	Example 295	Example 296	Example 297	Example 298
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A1	0.1	0.1	0.1	0.1	0.1	0.1		
	A2								
	A3								
	B1	0.5							
	B2		0.5						
	B3			0.5					
	B4				0.5				
	B5					0.5			
	B6						0.5		
	B7							0.5	
	B8								0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Anti-separation property 2		A	A	A	B	B	B	B	A
Stability 2		A	A	A	A	A	A	A	B

[Table 79]

		Example 346	Example 347	Example 348	Example 349	Example 350	Example 351	Example 352	Example 353
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	A2	-	-	-	-	-	-	-	-
	A3	-	-	-	-	-	-	-	-
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22
Anti-separation property 2		A	A	A	B	B	B	B	A
Stability 2		A	A	A	A	A	A	A	B

[Friction property evaluation test 2]

5 The frictional coefficients of the refrigerating machine oil compositions of Examples 174, 179, 230, 234, 284, 289, 339, 344, 394 and 399 were measured using an SRV tester by Optimol Inc., between a 1/2 inch SUJ2 steel ball and an SUJ2 disc ($\phi 10$ mm). The test

10 conditions were a load of 100 N, an amplitude of 1 mm and a frequency of 25Hz, and the frictional coefficient was recorded every second from the start of the test until 20 minutes thereafter, with the average being

15 taken as the mean frictional coefficient (hereinafter referred to as "mean frictional coefficient 2". The refrigerant was circulated to the slide member at a

flow rate of 10 L/h. The results are shown in Tables 80-81. In this test, the refrigerant type was selected depending on the type of base oil in the refrigerating machine oil composition. The refrigerant types used are shown in Tables 80-81.

5

[Table 80]

		Example 174	Example 179	Example 230	Example 234	Example 284	Example 289
Base oil		Base oil 1	Base oil 1	Base oil 3	Base oil 3	Base oil 2	Base oil 2
Additive (wt%)	A1	0.1	0.1	0.1	0.1	0.1	0.1
	A2	-	-	-	-	-	-
	A3	-	-	-	-	-	-
	B1	0.5	0.5	-	-	0.5	0.5
	B2	-	-	-	-	-	-
	B3	-	-	0.5	0.5	-	-
	B4	-	-	-	-	-	-
	B5	-	-	-	-	-	-
	B6	-	-	-	-	-	-
	B7	-	-	-	-	-	-
	B8	-	-	-	-	-	-
	C1	-	0.1	-	0.1	-	0.1
	C2	-	0.5	-	0.5	-	0.5
	C3	0.001	0.001	0.002	0.002	0.001	0.001
Refrigerant		R410A	R410A	R410A	R410A	R134a	R134a
Mean frictional coefficient 2		0.110	0.095	0.118	0.105	0.131	0.119

[Table 81]

		Example 339	Example 344	Example 394	Example 399
Base oil		Base oil 5	Base oil 5	Base oil 4	Base oil 4
Additive (wt%)	A1	0.1	0.1	0.1	0.1
	A2	-	-	-	-
	A3	-	-	-	-
	B1	0.5	0.5	0.5	0.5
	B2	-	-	-	-
	B3	-	-	-	-
	B4	-	-	-	-
	B5	-	-	-	-
	B6	-	-	-	-
	B7	-	-	-	-
	B8	-	-	-	-
	C1	-	0.1	-	0.1
	C2	-	0.5	-	0.5
	C3	0.001	0.001	0.001	0.001
Refrigerant		R134a	R134a	R22	R22
Mean frictional coefficient 2		0.139	0.128	0.118	0.107

[0245] [Examples 453-463]

5 Base oils 1-5 and additives A1, A4, B2, B4 and B6 were used to prepare the refrigerating machine oil compositions shown in Table 82.

[0246] [Anti-sludge property evaluation test]

10 The anti-sludge property of each of the refrigerating machine oil compositions of Examples 453-463 was measured by the following procedure. First, 1 g of chlorinated processed oil was added with respect to 99 g of the refrigerating machine oil composition. The water content of the test oil was adjusted to 100 ppm for Example 279 and Comparative Example 64, and to

15

500 ppm for all the other examples. Next, 100 g of the test oil was placed in a 300 ml autoclave together with each iron, copper or aluminum catalyst (1 mmφ x 10 cm each), and after deairing the autoclave, it was filled with 50 g of refrigerant. The combinations of refrigerating machine oil compositions and refrigerants are shown in Table 82. Each autoclave was held at 150°C for 14 days, and the presence of sludge was observed after the test. The results are shown in Table 82. Letter A in the tables indicates that no sludge was found, and B indicates that sludge was found.

[Table 82]

	Example 453	Example 454	Example 456	Example 457	Example 458	Example 459	Example 460	Example 461	Example 462	Example 463
Base oil	Base oil 1	Base oil 1	Base oil 2	Base oil 2	Base oil 3	Base oil 3	Base oil 4	Base oil 4	Base oil 5	Base oil 5
	-	0.5	-	0.5	-	0.5	-	0.5	-	0.5
Additive (wt%)	A1	-	0.5	-	0.5	-	0.5	-	0.5	-
	A4	0.5	-	0.5	-	0.5	0.5	-	-	0.5
	B2	0.5	0.5	-	-	0.5	0.5	0.5	0.5	-
	B6	-	-	0.5	0.5	-	-	0.5	0.5	-
Refrigerant	R410A	R410A	R134a	R134a	R410A	R410A	R22	R22	R134a	R134a
Anti-sludge property	A	B	A	B	A	B	A	B	A	B

[0247] [Examples 464-569]

For Examples 464-569, base oils 1-8 and additives A1, A4 and B1-B8 were used to prepare the refrigerating machine oil compositions shown in Tables 83-94 below. These refrigerating machine oil compositions contained both tricresyl phosphate (A1) and triphenyl

phosphorothionate (A4) as essential components.

[0248] Next, each of the refrigerating machine oil compositions of Examples 464-569 were subjected to the evaluation tests described below. The row "Refrigerant" in Tables 83-94 shows the type of refrigerant used in the evaluation test.

[0249] [Friction property and abrasion property evaluation test 1]

The slide member of a FALEX Tester (ASTM D2714) was set in a pressure-resistant vessel, the refrigerant was introduced into the vessel, and a FALEX test was carried out under the following conditions.

Test materials: Steel ring, steel block

Test initial temperature: 80°C

Test time: 1 hr

Sliding speed: 0.5 m/s

Load: 1250 N

Refrigerant atmosphere pressure: 500 kPa.

[0250] The frictional coefficient and oil temperature were measured every other second after the start of the FALEX test, and the mean values were calculated (hereinafter referred to as "mean frictional coefficient 1" and "mean oil temperature 1"). The block abrasion loss after completion of the test was determined in terms of volume reduction (hereinafter referred to as "abrasion volume 1"). The results are

shown in Tables 83-94.

[0251] [Friction property and abrasion property
evaluation test 3]

5 A FALEX test (ASTM D2670) was conducted under the
following conditions while blowing the refrigerant into
the refrigerating machine oil composition.

Test initial temperature: 25°C

Test time: 30 min

Load: 1334 N

10 Refrigerant blow-in rate: 10 L/h

[0252] The frictional coefficient and oil
temperature were measured every other second after the
start of the FALEX test, and the mean values were
calculated (hereinafter referred to as "mean frictional
coefficient 3" and "mean oil temperature 3"). The
15 weights of the pin and block were measured after
completion of the test, and the abrasion loss was
determined in terms of weight reduction (hereinafter
referred to as "abrasion loss 3"). The results are
20 shown in Tables 83-94.

[Table 83]

		Example 464	Example 465	Example 466	Example 467	Example 468	Example 469	Example 470	Example 471
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.11	0.10	0.14	0.13	0.15	0.15	0.14	0.14
Mean oil temp. 1 (°C)		84	85	85	94	95	93	92	91
Abrasion volume 1 (mm ³)		1.7	1.9	2.0	2.3	2.4	2.4	2.5	2.6
Mean frictional coefficient 3		0.102	0.101	0.103	0.101	0.111	0.112	0.109	0.110
Mean oil temp. (°C) 3		45	45	47	46	46	52	50	50
Abrasion loss 3 (mg)		7.0	6.9	7.2	7.8	8.1	8.0	8.2	8.1

[Table 84]

		Example 472	Example 473	Example 474	Example 475	Example 476	Example 477	Example 478	Example 479
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R410A	R410A	R410A	R410A	R410A	R410A	R410A	R410A
Mean frictional coefficient 1		0.12	0.13	0.12	0.11	0.14	0.15	0.12	0.14
Mean oil temp. 1 (°C)		94	92	91	91	93	93	94	92
Abrasion volume 1 (mm ³)		2.2	2.4	2.5	2.7	2.9	2.8	3.0	2.9
Mean frictional coefficient 3		0.104	0.106	0.109	0.105	0.117	0.116	0.114	0.110
Mean oil temp. (°C) 3		44	46	46	46	43	46	47	48
Abrasion loss 3 (mg)		8.1	7.8	8.2	8.8	8.9	9.0	9.3	9.4

{Table 85}

		Example 480	Example 481	Example 482	Example 483	Example 484	Example 485	Example 486	Example 487
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.10	0.13	0.12	0.13	0.16	0.17	0.18	0.17
Mean oil temp. 1 (°C)		85	86	86	92	91	94	93	93
Abrasion volume 1 (mm ³)		2.6	2.8	2.9	2.8	3.0	3.3	3.1	3.0
Mean frictional coefficient 3		0.104	0.110	0.108	0.108	0.120	0.123	0.115	0.117
Mean oil temp. 3 (°C)		47	48	47	48	47	51	49	50
Abrasion loss 3 (mg)		7.6	8.3	8.5	8.7	9.0	8.9	8.8	9.1

[Table 86]

		Example 488	Example 489	Example 500	Example 501	Example 502	Example 503	Example 504	Example 505
Base oil		Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5	Base oil 5
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R134a	R134a	R134a	R134a	R134a	R134a	R134a	R134a
Mean frictional coefficient 1		0.11	0.13	0.13	0.13	0.15	0.16	0.15	0.13
Mean oil temp. 1 (°C)		84	85	87	91	90	90	89	90
Abrasion volume 1 (mm ³)		2.8	2.9	2.8	3.6	3.5	3.4	3.5	3.2
Mean frictional coefficient 3		0.106	0.111	0.108	0.107	0.115	0.116	0.110	0.112
Mean oil temp. 3 (°C)		44	45	45	45	46	48	49	48
Abrasion loss 3 (mg)		9.3	9.5	9.5	9.9	10.3	10.4	10.3	10.0

[Table 87]

		Example 506	Example 507	Example 508	Example 509	Example 510	Example 511	Example 512	Example 513
Base oil		Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4	Base oil 4
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R22	R22	R22	R22	R22	R22	R22	R22
Mean frictional coefficient 1		0.10	0.11	0.12	0.11	0.13	0.12	0.13	0.14
Mean oil temp. 1 (°C)		84	85	86	87	87	86	88	91
Abrasion volume 1 (mm ³)		1.6	1.8	1.7	1.9	2.0	2.0	1.8	2.01
Mean frictional coefficient 3		0.111	0.113	0.114	0.111	0.120	0.119	0.114	0.116
Mean oil temp. 3 (°C)		47	48	49	48	47	50	51	51
Abrasion loss 3 (mg)		7.6	7.8	7.7	8.2	8.3	8.2	8.4	8.5

[Table 88]

		Example 514	Example 515	Example 516	Example 517	Example 518	Example 519	Example 520	Example 521
Base oil		Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1	Base oil 1
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R407C	R407C	R407C	R407C	R407C	R407C	R407C	R407C
Mean frictional coefficient 1		0.11	0.10	0.13	0.13	0.15	0.14	0.14	0.14
Mean oil temp. 1 (°C)		84	85	85	92	92	91	92	90
Abrasion volume 1 (mm ³)		1.1	1.2	1.4	1.8	1.9	1.9	2.0	2.1
Mean frictional coefficient 3		0.102	0.102	0.103	0.103	0.115	0.113	0.107	0.110
Mean oil temp. 3 (°C)		45	45	46	46	47	50	50	51
Abrasion loss 3 (mg)		7.0	7.2	7.6	7.8	8.3	8.0	8.2	8.3

[Table 89]

		Example 522	Example 523	Example 524	Example 525	Example 526	Example 527	Example 528	Example 529
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R407C	R407C	R407C	R407C	R407C	R407C	R407C	R407C
Mean frictional coefficient 1		0.12	0.13	0.12	0.11	0.14	0.14	0.12	0.14
Mean oil temp. 1 (°C)		92	92	91	91	93	93	93	92
Abrasion volume 1 (mm ³)		1.8	2.0	2.1	2.2	2.5	2.6	2.8	2.7
Mean frictional coefficient 3		0.106	0.106	0.107	0.107	0.113	0.114	0.112	0.113
Mean oil temp. 3 (°C)		45	46	46	46	47	47	49	50
Abrasion loss 3 (mg)		8.0	8.2	8.5	8.8	9.2	9.1	9.3	9.2

[Table 90]

		Example 530	Example 531	Example 532	Example 533	Example 534	Example 535	Example 536	Example 537
Base oil		Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2	Base oil 2
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	0.5	-
Refrigerant		CO2	CO2	CO2	CO2	CO2	CO2	CO2	CO2
Mean frictional coefficient 1		0.10	0.13	0.12	0.13	0.15	0.16	0.17	0.16
Mean oil temp. 1 (°C)		85	86	86	91	91	92	93	91
Abrasion volume 1 (mm ³)		2.3	2.5	2.5	2.6	2.7	2.9	2.7	2.8
Mean frictional coefficient 3		0.103	0.105	0.108	0.109	0.118	0.121	0.113	0.112
Mean oil temp. 3 (°C)		48	49	49	49	50	51	51	52
Abrasion loss 3 (mg)		7.7	8.6	8.3	9.0	9.1	9.3	9.2	9.4

[Table 91]

		Example 538	Example 539	Example 540	Example 541	Example 542	Example 543	Example 544	Example 545
Base oil		Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6	Base oil 6
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		CO2	CO2	CO2	CO2	CO2	CO2	CO2	CO2
Mean frictional coefficient 1		0.12	0.11	0.13	0.14	0.10	0.13	0.14	0.13
Mean oil temp. 1 (°C)		84	85	85	91	92	91	92	90
Abrasion volume 1 (mm ³)		1.2	1.2	1.4	1.9	2.0	1.9	2.2	2.2
Mean frictional coefficient 3		0.111	0.112	0.113	0.114	0.119	0.120	0.118	0.119
Mean oil temp. 3 (°C)		47	46	47	48	49	50	51	52
Abrasion loss 3 (mg)		7.5	7.3	7.8	8.2	8.4	8.3	8.4	8.5

[Table 92]

		Example 546	Example 547	Example 548	Example 549	Example 550	Example 551	Example 552	Example 553
Base oil		Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3	Base oil 3
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂	CO ₂
Mean frictional coefficient 1		0.12	0.13	0.12	0.11	0.14	0.14	0.12	0.13
Mean oil temp. 1 (°C)		92	92	91	91	93	93	94	92
Abrasion volume 1 (mm ³)		1.8	2.2	2.2	2.4	2.5	2.4	2.7	2.5
Mean frictional coefficient 3		0.106	0.108	0.110	0.110	0.117	0.117	0.114	0.115
Mean oil temp. 3 (°C)		46	46	47	48	48	49	50	51
Abrasion loss 3 (mg)		8.1	8.1	8.2	8.8	8.9	8.7	8.9	9.0

[Table 93]

		Example 554	Example 555	Example 556	Example 557	Example 558	Example 559	Example 560	Example 561
Base oil		Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7	Base oil 7
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R290	R290	R290	R290	R290	R290	R290	R290
Mean frictional coefficient 1		0.13	0.14	0.13	0.12	0.15	0.15	0.13	0.14
Mean oil temp. 1 (°C)		92	92	91	91	93	93	94	92
Abrasion volume 1 (mm ³)		1.7	2.0	2.1	2.2	2.3	2.2	2.4	2.3
Mean frictional coefficient 3		0.093	0.094	0.094	0.095	0.102	0.101	0.099	0.100
Mean oil temp. 3 (°C)		44	44	46	45	47	48	49	50
Abrasion loss 3 (mg)		7.1	7.2	7.5	7.8	8.0	7.8	8.0	8.1

[Table 94]

		Example 562	Example 563	Example 564	Example 565	Example 566	Example 567	Example 568	Example 569
Base oil		Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8	Base oil 8
Additive (wt%)	A1	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	A4	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	B1	0.5	-	-	-	-	-	-	-
	B2	-	0.5	-	-	-	-	-	-
	B3	-	-	0.5	-	-	-	-	-
	B4	-	-	-	0.5	-	-	-	-
	B5	-	-	-	-	0.5	-	-	-
	B6	-	-	-	-	-	0.5	-	-
	B7	-	-	-	-	-	-	0.5	-
	B8	-	-	-	-	-	-	-	0.5
Refrigerant		R600a	R600a	R600a	R600a	R600a	R600a	R600a	R600a
Mean frictional coefficient 1		0.11	0.11	0.12	0.11	0.12	0.12	0.12	0.12
Mean oil temp. 1 (°C)		92	92	91	91	93	93	94	92
Abrasion volume 1 (mm ³)		1.9	2.3	2.3	2.4	2.6	2.4	2.8	2.6
Mean frictional coefficient 3		0.105	0.108	0.109	0.107	0.120	0.119	0.118	0.116
Mean oil temp. 3 (°C)		48	49	50	50	51	51	54	53
Abrasion loss 3 (mg)		7.1	6.9	7.2	7.8	8.1	8.0	8.1	8.2

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

